




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
TORONTO LUBE SERVICE
 Machine Id
9998 (S/N 54287336)
 Component
Hydraulic System
 Fluid
ALLIED HYDRAULIC AW46 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.
 NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC0925569	WC0925570	---
Sample Date	Client Info			11 Jun 2024	30 May 2024	---
Machine Age	hrs	Client Info		20	4	---
Oil Age	hrs	Client Info		0	4	---
Oil Changed	Client Info			Not Chngd	Not Chngd	---
Sample Status				NORMAL	SEVERE	---

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method		>0.05	NEG	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	0	<1	---
Chromium	ppm	ASTM D5185(m)	>20	0	0	---
Nickel	ppm	ASTM D5185(m)	>20	<1	0	---
Titanium	ppm	ASTM D5185(m)		0	0	---
Silver	ppm	ASTM D5185(m)		0	0	---
Aluminum	ppm	ASTM D5185(m)	>20	0	0	---
Lead	ppm	ASTM D5185(m)	>20	0	0	---
Copper	ppm	ASTM D5185(m)	>20	<1	<1	---
Tin	ppm	ASTM D5185(m)	>20	0	0	---
Antimony	ppm	ASTM D5185(m)		0	0	---
Vanadium	ppm	ASTM D5185(m)		0	0	---
Beryllium	ppm	ASTM D5185(m)		0	0	---
Cadmium	ppm	ASTM D5185(m)		0	0	---





ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1	1	---
Barium	ppm	ASTM D5185(m)		<1	<1	---
Molybdenum	ppm	ASTM D5185(m)		0	0	---
Manganese	ppm	ASTM D5185(m)		0	0	---
Magnesium	ppm	ASTM D5185(m)		2	2	---
Calcium	ppm	ASTM D5185(m)		57	56	---
Phosphorus	ppm	ASTM D5185(m)		331	321	---
Zinc	ppm	ASTM D5185(m)		425	407	---
Sulfur	ppm	ASTM D5185(m)		761	903	---
Lithium	ppm	ASTM D5185(m)		<1	<1	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	<1	0	---
Sodium	ppm	ASTM D5185(m)		0	0	---
Potassium	ppm	ASTM D5185(m)	>20	0	0	---

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	1492	▲ 42439	---
Particles >6µm		ASTM D7647	>1300	166	▲ 6533	---
Particles >14µm		ASTM D7647	>160	33	● 263	---
Particles >21µm		ASTM D7647	>40	13	52	---
Particles >38µm		ASTM D7647	>10	1	2	---
Particles >71µm		ASTM D7647	>3	0	1	---
Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/15/12	▲ 23/20/15	---



OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.38	0.37	---





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	NORML	---
Emulsified Water	scalar	Visual*	>0.05	NEG	NEG	---
Free Water	scalar	Visual*		NEG	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)		43.4	43.0	---

SAMPLE IMAGES



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0925569 **Received** : 17 Jun 2024
Lab Number : **02642326** **Tested** : 18 Jun 2024
Unique Number : 5799865 **Diagnosed** : 18 Jun 2024 - Wes Davis
Test Package : IND 2

SAMCO MACHINERY LTD
 351 PASSMORE AVE
 TORONTO, ON
 CA M1V 3N8
 Contact: Louie Partalis
 LPartalis@samco-machinery.com
 T: (416)523-1097
 F: (416)285-7469

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.