




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

EXTRUDEUSE KRAUSS-MAFFEI

Machine Id

121424: REDUCTEUR, PRIMAIRE ZE90 (S/N 90335702)

Component

Reduction Gear

Fluid

CHEVRON MEROPA SYNTHETIC WM 320 (270 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			CB0031938	CB0031828	CB0031636
Sample Date	Client Info			17 Jun 2024	23 Apr 2024	01 Feb 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	Client Info			N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method		>0.1	NEG	NEG	NEG





WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>150	4	3	3
Chromium	ppm	ASTM D5185(m)	>10	0	0	0
Nickel	ppm	ASTM D5185(m)	>10	<1	0	0
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)		0	0	0
Aluminum	ppm	ASTM D5185(m)	>25	<1	0	<1
Lead	ppm	ASTM D5185(m)	>100	<1	0	<1
Copper	ppm	ASTM D5185(m)	>50	1	2	2
Tin	ppm	ASTM D5185(m)	>10	0	0	0
Antimony	ppm	ASTM D5185(m)	>5	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		24	25	26
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		0	0	0
Manganese	ppm	ASTM D5185(m)		0	0	0
Magnesium	ppm	ASTM D5185(m)		<1	0	0
Calcium	ppm	ASTM D5185(m)		2	1	1
Phosphorus	ppm	ASTM D5185(m)		231	229	232
Zinc	ppm	ASTM D5185(m)		2	1	<1
Sulfur	ppm	ASTM D5185(m)		6388	5933	6567
Lithium	ppm	ASTM D5185(m)		<1	<1	<1

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	1	0	1
Sodium	ppm	ASTM D5185(m)		<1	<1	<1
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	2

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	12353	10382	13905
Particles >6µm		ASTM D7647	>5000	2407	1745	2140
Particles >14µm		ASTM D7647	>640	183	108	136
Particles >21µm		ASTM D7647	>160	39	24	33
Particles >38µm		ASTM D7647	>40	3	3	4
Particles >71µm		ASTM D7647	>10	1	1	2
Oil Cleanliness		ISO 4406 (c)	>21/19/16	21/18/15	21/18/14	21/18/14

OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.7	0.51	0.50	0.52





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	320	319	320	320

SAMPLE IMAGES



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : CB0031938 **Received** : 18 Jun 2024
Lab Number : **02642675** **Tested** : 19 Jun 2024
Unique Number : 5800214 **Diagnosed** : 19 Jun 2024 - Wes Davis
Test Package : IND 2

Owens Corning Celfortec LP
 542, rue Gaetan
 Salaberry de Valleyfield, QC
 CA J6S 0A7
 Contact: Hugo Duguay
 hugo.duguay@owenscorning.com
 T: (450)377-1725 E X:T 7531
 F: (450)377-2973

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.