

## **OIL ANALYSIS REPORT**

Sample Rating Trend



### Area **Jobal - J00400 A2406127**

Hydraulic System Fluid CHEM-ECOL WAYLUBE 68 (--- GAL)

#### DIAGNOSIS

#### Recommendation

We certify that this oil is clean, that the additives are at acceptable levels, and that it is suitable for use.


#### Contamination


Silicon ppm levels are notably high.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Batch #		Client Info		2024 05 0690		
Department		Client Info		Production		
Sample From		Client Info		Machine		
Production Stage		Client Info		Final		
Sent to WC		Client Info		06/19/2024		
Sample Number		Client Info		E30002449		
Sample Date		Client Info		19 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	8		
Chromium	ppm	ASTM D5185(m)	>20	0		
Nickel	ppm	ASTM D5185(m)	>20	2		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	( )	>20	1		
Lead	ppm	ASTM D5185(m) ASTM D5185(m)	>20	0		
Copper Tin	ppm	ASTM D5185(m) ASTM D5185(m)	>20 >20	7 0		
Antimony	ppm ppm	ASTM D5185(m)	>20	0		
Vanadium	ppm	ASTM D5185(m)		۲ ۲		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		1		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)		2		
Calcium	ppm	ASTM D5185(m)		13		
Phosphorus	ppm	ASTM D5185(m)		189		
Zinc	ppm	ASTM D5185(m)		52		
Sulfur	ppm	ASTM D5185(m)		2221		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	24		
Sodium	ppm	ASTM D5185(m)		5		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water	%	ASTM D6304*	>0.05	0.00		
ppm Water	ppm	ASTM D6304*	>500	0		



# **OIL ANALYSIS REPORT**








FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	444		
Particles >6µm		ASTM D7647	>640	93		
Particles >14µm		ASTM D7647	>160	9		
Particles >21µm		ASTM D7647	>40	3		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	1		
Oil Cleanliness		ISO 4406 (c)	>19/16/14	16/14/10		
FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.75		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.05	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	68	68.5		
Visc @ 100°C	cSt	ASTM D7279(m)		9.5		
Viscosity Index (VI)	Scale	ASTM D2270*		117		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image





Report Id: CHECOB [WCAMIS] 02643421 (Generated: 06/25/2024 10:27:34) Rev: 1

Contact/Location: Tatiana Sorkina - CHECOB