

OIL ANALYSIS REPORT

Area MINING Machine Id ME-587 JOHN DEERE 944K 1DW944KXTNL703685

Rear Left Final Drive

Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.



Sample Rating Trend



NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0946257		
Sample Date		Client Info		19 Jun 2024		
Machine Age	hrs	Client Info		6919		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	۷	method	limit/base	current	history1	history2
Water		WC Method	>0.075	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>750	6		
Chromium	ppm	ASTM D5185(m)	>9	0		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>40	<1		
Lead	ppm	ASTM D5185(m)	>15	<1		
Copper	ppm	ASTM D5185(m)	>40	21		
Tin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		3		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		<1		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		29		
Calcium	ppm	ASTM D5185(m)		2691		
Phosphorus	ppm	ASTM D5185(m)		948		
Zinc	ppm	ASTM D5185(m)		1027		
Sulfur	ppm	ASTM D5185(m)		2810		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	11		
Sodium	ppm	ASTM D5185(m)	>51	<1		
Potassium	ppm	ASTM D5185(m)	>20	0		



OIL ANALYSIS REPORT

	osity @ 40°C	
160 Abnor	mal	
140		
្ឆ ¹²⁰		
()-0(+) ()-0(+)(-)(-)(+)(+)(+)(+)(+)(+)(+)(+)(+)(+)(+)(+)(+)	mal	
60		
40		
Jun19/2 [,]		Jun19/2 ⁴

	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
	Precipitate	scalar	Visual*	NONE	NONE		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
Jun19/24 -	Appearance	scalar	Visual*	NORML	NORML		
Junl	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.075	NEG		
	Free Water	scalar	Visual*		NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m	1)	49.8		
	SAMPLE IMAGES	6	method	limit/base	current	history1	history2
	Color					no image	no image
	Bottom					no image	no image
	Ferrous Alloys			Jun19/24			
Laboratory Sample No. Lab Number Unique Number Test Package		Appleby Recei Teste Diagr	ved : 2 d : 2	ington, ON L7L 21 Jun 2024 21 Jun 2024 21 Jun 2024 - Kev	2	60 Unimin Road,	via Canada Ltd. County Rd. #46 Havelock, ON CA K0L 1Z0 potact: Dan Lyon

 Laboratory
 Test Package
 : CONST

 To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

 Validity of results and interpretation are based on the sample and information as supplied.

Havelock, ON Havelock, ON CA K0L 1Z0 Contact: Dan Lyon dan.lyon@coviacorp.com T: (705)632-8904 F:

Contact/Location: Dan Lyon - COVHAV

Report Id: COVHAV [WCAMIS] 02643454 (Generated: 06/21/2024 16:17:13) Rev: 1

CALA

ISO 17025:2017

Accredited Laboratory

Page 2 of 2