

# **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL



#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the fluid.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0904451		
Sample Date		Client Info		24 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	I	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>230	42		
Chromium	ppm	ASTM D5185(m)	>2	<1		
Nickel	ppm	ASTM D5185(m)	>5	<1		
Titanium	ppm	ASTM D5185(m)	>2	0		
Silver	ppm	ASTM D5185(m)	>5	0		
Aluminum	ppm	ASTM D5185(m)	>65	5		
Lead	ppm	ASTM D5185(m)	>55	2		
Copper	ppm	ASTM D5185(m)	>85	17		
Tin	ppm	ASTM D5185(m)	>5	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		56		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)		4		
Calcium	ppm	ASTM D5185(m)		85		
Phosphorus	ppm	ASTM D5185(m)		163		
Zinc	ppm	ASTM D5185(m)		16		
Sulfur	ppm	ASTM D5185(m)		1551		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>20	5		
Sodium	ppm	ASTM D5185(m)		11		
Potassium	ppm	ASTM D5185(m)	>20	7		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.73		



# **OIL ANALYSIS REPORT**



	VISUAL		method				history2
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
	Precipitate	scalar	Visual*	NONE	NONE		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	VLITE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
124/24	Appearance	scalar	Visual*	NORML	NORML		
Jun	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.1	NEG		
	Free Water	scalar	Visual*		NEG		
	FLUID PROPERT	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)		28.7		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Jun24/24	Color					no image	no image
	Bottom					no image	no image
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	400 Severe			100	Severe		
	8 200 - <b>P</b>			툡 50			
	0				,		
	n24/24			n24/24	n24/24		n24/24
	⊰ Aluminum (ppm)			ηr	⊰ Chromium (pr	om)	٦٢
	150 Severe		10	, 			
	Abnormal			ud S	Severe		
	0				Abnormal		
	24/24			4/24	. 4/24 .		:4/24 .
	Jun			Junt	Juni		շոր
	Copper (ppm)				Silicon (ppm)		
				40	Severe		
				틆 20	) - Abnormal		-
	0			(			
	n24/2			n24/2	n24/2		n24/2
	5			٦٢	n L		nr
	Viscosity @ 40°C				Acid Number		
	2 35 Abnormal			Bu			
	ද් 30 - Abnormal				1		
	25			24 +			24 +
	Jun24			Jun24,	Jun24		Jun24,
Laboratory Sample No. Lab Number Unique Number Test Package	: WearCheck - C8-1175 : WC0904451 : 02644393 : 5801932 : MOB 2 ( Additional Te	5 Appleb Rece Teste Diagi ests: TAN	y Line, Burlin ived : 27 ed : 27 nosed : 27 I Man ) 800-268-212	ngton, ON L7I 7 Jun 2024 7 Jun 2024 Jun 2024 - Kev 1	L 5H9 in Marson	VEHICLE FO NIAGA Contac	RENSICS INC. PO BOX 40047 RA FALLS, ON CA L2E 0A3 ct: Ryan Cockle

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Contact/Location: Ryan Cockle - VEHNIA Page 2 of 2

T: (289)843-7402

F:



CALA

ISO 17025:2017 Accredited Laboratory