

OIL ANALYSIS REPORT

Area (C-FAFM) [C-FAFM] BEECHCRAFT KING AIR 200 PCE-94144

Left Jet Turbine

Fluid EASTMAN TURBO OIL 2380 (--- QTS)

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear


All component wear rates are normal. The ferrography results are normal indicating no abnormal wear in the system.

Contaminants

The water content is negligible. There is no indication of any contamination in the oil.

Oil Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0957301		
Sample Date		Client Info		27 Jun 2024		
TSN	hrs	Client Info		10089		
TSO	hrs	Client Info		3594		
Oil Age	hrs	Client Info		112		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>8	0		
Chromium	ppm	ASTM D5185(m)	>2	0		
Nickel	ppm	ASTM D5185(m)	>2	<1		
Titanium	ppm	ASTM D5185(m)	>2	0		
Silver	ppm	ASTM D5185(m)	>2	0		
Aluminum	ppm	ASTM D5185(m)	>2	<1		
Lead	ppm	ASTM D5185(m)	>3	0		
Copper	ppm	ASTM D5185(m)	>3	<1		
Tin	ppm	ASTM D5185(m)	>2	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	<1		
Barium	ppm	ASTM D5185(m)	0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)	0	<1		
Calcium	ppm	ASTM D5185(m)	0	0		
Phosphorus	ppm	ASTM D5185(m)	2500	2608		
Zinc	ppm	ASTM D5185(m)	0	9		
Sulfur	ppm	ASTM D5185(m)	0	10		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>8	6		
Sodium	ppm	ASTM D5185(m)		0		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water	%	ASTM D6304*	>0.1	0.092		
ppm Water	ppm	ASTM D6304*	>1000	930		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.43	0.35		


Sample Rating Trend



22 Abnorma

21 20. Jun27/24

OIL ANALYSIS REPORT



	VISUAL		method	limit/base	e current	history1	history2
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
	Precipitate	scalar	Visual*	NONE	NONE		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
Jun27/24	Appearance	scalar	Visual*	NORML	NORML		
Jur	Odor	scalar	Visual*	NORML	NORML		
°C	Emulsified Water	scalar	Visual*	>0.1	NEG		
1	Free Water	scalar	Visual*		NEG		
	FLUID PROPERT	IES	method	limit/base	e current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)	24.2	24.3		
	Visc @ 100°C	cSt	ASTM D7279(m)	4.97	4.9		
	Viscosity Index (VI)	Scale	ASTM D2270*	134	127		
	SAMPLE IMAGES	3	method	limit/base	e current	history1	history2
Jun27/24		, 	method	initi basi		Thotory I	motoryz
•C	Color					no image	no image
	Bottom					no image	no image
C	Non-ferrous Metals	5		Jun27/24 Jun	Acid Number		Jun27/24
Laboratory Sample No. Lab Number Unique Number Test Package To discuss this sample report, Test denoted (*) outside scop Validity of results and interpret	: 5802352 : AVI 3 . contact Customer Servi e of accreditation, (m) me	Recei Teste Diagr ce at 1-8 ethod mo	ived : 02 ed : 03 nosed : 08 800-268-213 polified, (e) te	2 Jul 2024 3 Jul 2024 Jul 2024 - K 1. ested at exte	evin Marson ernal lab.	80 HANG/ V Contact: D denis.bourgouin T:	FAST AIR LTD AR LINE ROAD VINNIPEG, ME CA R3J 3Y7 enis Bourgouir @flyfastair.com (204)772-7622 (204)783-2483

Report Id: FASWIN [WCAMIS] 02644813 (Generated: 07/08/2024 15:47:41) Rev: 1


Contact/Location: Denis Bourgouin - FASWIN

FERROGRAPHY REPORT

Area (C-FAFM) [C-FAFM] BEECHCRAFT KING AIR 200 PCE-94144

Left Jet Turbine


Fluid EASTMAN TURBO OIL 2380 (--- QTS)



DR-FERROGRAPHY		method	limit/base	current	history1	history2
Large Particles		DR-Ferr*		1.0		
Small Particles		DR-Ferr*		0.4		
Total Particles		DR-Ferr*	>	1.4		
Large Particles Percentage	%	DR-Ferr*		42.9		
Severity Index		DR-Ferr*		1		
FERROGRAPHY		method	limit/base	current	history1	history2
Ferrous Rubbing	Scale 0-10	ASTM D7684*		1		
Ferrous Sliding	Scale 0-10	ASTM D7684*				
Ferrous Cutting	Scale 0-10	ASTM D7684*				
Ferrous Rolling	Scale 0-10	ASTM D7684*				
Ferrous Break-in	Scale 0-10	ASTM D7684*				
Ferrous Spheres	Scale 0-10	ASTM D7684*				
Ferrous Black Oxides	Scale 0-10	ASTM D7684*				
Ferrous Red Oxides	Scale 0-10	ASTM D7684*				
Ferrous Corrosive	Scale 0-10	ASTM D7684*				
Ferrous Other	Scale 0-10	ASTM D7684*				
Nonferrous Rubbing	Scale 0-10	ASTM D7684*				
Nonferrous Sliding	Scale 0-10	ASTM D7684*				
Nonferrous Cutting	Scale 0-10	ASTM D7684*				
Nonferrous Rolling	Scale 0-10	ASTM D7684*				
Nonferrous Other	Scale 0-10	ASTM D7684*				
Carbonaceous Material	Scale 0-10	ASTM D7684*				
Lubricant Degradation	Scale 0-10	ASTM D7684*				
Sand/Dirt	Scale 0-10	ASTM D7684*				
Fibres	Scale 0-10	ASTM D7684*				
Spheres	Scale 0-10	ASTM D7684*		_		
Other	Scale 0-10	ASTM D7684*		1		

WEAF

All component wear rates are normal. The ferrography results are normal indicating no abnormal wear in the system.



This page left intentionally blank