

## **OIL ANALYSIS REPORT**

Machine ID

Department

Sent to WC

Machine Age

Oil Age

Sample From

**Production Stage** 

Sample Number Sample Date

hrs

**Client Info** 

### Area **Arvin Sango - 888103 RB051**

Hydraulic System CATALYS HYDRAULIC AW 46 (--- GAL)

### Recommendation

We certify that this oil is clean, that the additives are at acceptable levels, and that it is suitable for use.

Contamination

Potassium ppm levels are noted.



Sample Rating Trend

Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	<1		
Chromium	ppm	ASTM D5185(m)	>20	0		
Nickel	ppm	ASTM D5185(m)	>20	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>20	<1		
Lead	ppm	ASTM D5185(m)	>20	0		
Copper	ppm	ASTM D5185(m)	>20	2		
Tin	ppm	ASTM D5185(m)	>20	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		


0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		39		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		1		
Calcium	ppm	ASTM D5185(m)		69		
Phosphorus	ppm	ASTM D5185(m)		354		
Zinc	ppm	ASTM D5185(m)		436		
Sulfur	ppm	ASTM D5185(m)		833		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	0		
Sodium	ppm	ASTM D5185(m)		2		
Potassium	ppm	ASTM D5185(m)	>20	17		
Water	%	ASTM D6304*	>0.05	0.002		
ppm Water	ppm	ASTM D6304*	>500	19		


NORMAL





# **OIL ANALYSIS REPORT**












FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	809		
Particles >6µm		ASTM D7647	>640	231		
Particles >14µm		ASTM D7647	>160	24		
Particles >21µm		ASTM D7647	>40	7		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	1		
Oil Cleanliness		ISO 4406 (c)	>19/16/14	17/15/12		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.40		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.05	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	46.9	46.6		
Visc @ 100°C	cSt	ASTM D7279(m)	6.9	6.9		
Viscosity Index (VI)	Scale	ASTM D2270*	102	103		
SAMPLE IMAGES	3	method	limit/base	current	history1	history2





Report Id: CHECOB [WCAMIS] 02646223 (Generated: 07/10/2024 14:16:19) Rev: 1

Contact/Location: Tatiana Sorkina - CHECOB

no image

no image

no image

no image