


OIL ANALYSIS REPORT

Area MINING Machine Id ME-586 JOHN DEERE 944K 1DW944KXPNL703686

Front Right Final Drive

Fluid SHELL Spirax S4 CX 30 (--- GAL)


DIAGNOSIS



SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0942058		
Sample Date		Client Info		02 Jul 2024		
Machine Age	hrs	Client Info		3191		
Oil Age	hrs	Client Info		3191		
Oil Changed		Client Info		Not Changd		
Sample Status				ABNORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.075	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>750	12		
Chromium	ppm	ASTM D5185(m)	>9	0		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		<1		
Aluminum	ppm	ASTM D5185(m)	>40	<1		
Lead	ppm	ASTM D5185(m)	>15	<1		
Copper	ppm	ASTM D5185(m)	>40	32		
Tin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		3		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		<1		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)		52		
Calcium	ppm	ASTM D5185(m)		3156		
Phosphorus	ppm	ASTM D5185(m)		1095		
Zinc	ppm	ASTM D5185(m)		1219		
Sulfur	ppm	ASTM D5185(m)		3428		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	26		
Sodium	ppm	ASTM D5185(m)	>51	2		
Potassium	ppm	ASTM D5185(m)	>20	<1		



OIL ANALYSIS REPORT



		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.075	NEG		
Free Water	scalar	Visual*	20.070	NEG		
FLUID PROPERT		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)		47.4		
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
	,	method			Thotory I	Thotory 2
Color				J.	no image	no image
			69		no imago	no inago
Bottom						
DOLLOIN					no image	no image
GRAPHS						
Ferrous Alloys						
Ferrous Alloys						
Ferrous Alloys						
Ferrous Alloys						
Ferrous Alloys						
Ferrous Alloys						
Ferrous Alloys			2/24			
Ferrous Alloys			Jul2/24			
Ferrous Alloys	s		Jul2/24			
Ferrous Alloys	s		Jui2/24			
Ferrous Alloys	s		Jui224			
Ferrous Alloys	s		Jui2/24			
Ferrous Alloys	s		Jui2/24			
Ferrous Alloys	s		Jui2/24			
Ferrous Alloys	s					
Ferrous Alloys	s		Jul2/24			
Ferrous Alloys	5					
Ferrous Alloys	S					
Ferrous Alloys	S					
Ferrous Alloys	s					
Ferrous Alloys	S					
Ferrous Alloys	S					
Ferrous Alloys	S		Jul2/24			
Ferrous Alloys	S					



Laboratory CALA Sample No. : WC0942058 Lab Number : 02646354 ISO 17025:2017 Accredited Laboratory Unique Number : 5811906 Test Package : CONST

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 08 Jul 2024 Tested : 08 Jul 2024 : 09 Jul 2024 - Kevin Marson Diagnosed

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Covia Canada Ltd. 260 Unimin Road, County Rd. #46 Havelock, ON CA KOL 1Z0 Contact: Dan Lyon dan.lyon@coviacorp.com T: (705)632-8904 F:

Report Id: COVHAV [WCAMIS] 02646354 (Generated: 07/09/2024 08:33:59) Rev: 1

```
Submitted By: Paul Laneville
    Page 2 of 2
```