




# OIL ANALYSIS REPORT

## Sample Rating Trend



**NORMAL**



Machine Id

**9**

Component

**Air Compressor**

Fluid

**INGERSOLL-RAND SSR ULTRA COOLANT (--- GAL)**

### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

#### Wear

All component wear rates are normal.

#### Contamination

The water content is negligible. There is no indication of any contamination in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

### SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>PP</b>	PP	WC00229873
Sample Date	Client Info		<b>29 Jun 2024</b>	08 Apr 2024	09 May 1995
Machine Age	hrs	Client Info	<b>0</b>	0	-1
Oil Age	hrs	Client Info	<b>0</b>	0	0
Oil Changed	Client Info		<b>N/A</b>	N/A	---
Sample Status			<b>NORMAL</b>	NORMAL	---

### WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		<b>0</b>	0	---
Iron	ppm	ASTM D5185(m) >50	<b>&lt;1</b>	0	<1
Chromium	ppm	ASTM D5185(m) >4	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m) >4	<b>&lt;1</b>	0	<1
Titanium	ppm	ASTM D5185(m)	<b>0</b>	0	---
Silver	ppm	ASTM D5185(m)	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185(m) >10	<b>0</b>	0	0
Lead	ppm	ASTM D5185(m) >20	<b>0</b>	0	<1
Copper	ppm	ASTM D5185(m) >40	<b>&lt;1</b>	<1	2
Tin	ppm	ASTM D5185(m) >5	<b>0</b>	0	<1
Antimony	ppm	ASTM D5185(m)	<b>0</b>	0	---
Vanadium	ppm	ASTM D5185(m)	<b>0</b>	0	---
Beryllium	ppm	ASTM D5185(m)	<b>0</b>	0	---
Cadmium	ppm	ASTM D5185(m)	<b>0</b>	0	---

### ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0	<b>2</b>	<1	<1
Barium	ppm	ASTM D5185(m) 500	<b>811</b>	872	---
Molybdenum	ppm	ASTM D5185(m) 0	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)	<b>0</b>	0	---
Magnesium	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	0	<1
Calcium	ppm	ASTM D5185(m) 0	<b>1</b>	<1	67
Phosphorus	ppm	ASTM D5185(m) 20	<b>&lt;1</b>	0	341
Zinc	ppm	ASTM D5185(m) 0	<b>1</b>	1	391
Sulfur	ppm	ASTM D5185(m) 200	<b>208</b>	229	---
Lithium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	---

### CONTAMINANTS





	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >25	<b>6</b>	0	<1
Sodium	ppm	ASTM D5185(m)	<b>1</b>	1	<1
Potassium	ppm	ASTM D5185(m) >20	<b>&lt;1</b>	1	<1
Water	%	ASTM D6304* >0.6	<b>0.215</b>	0.001	---
ppm Water	ppm	ASTM D6304* >6000	<b>2153</b>	3	---

### FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	<b>0.03</b>	0.01	---




# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE
Precipitate	scalar	Visual*	NONE	<b>NONE</b>	NONE
Silt	scalar	Visual*	NONE	<b>NONE</b>	NONE
Debris	scalar	Visual*	NONE	<b>NONE</b>	VLITE
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	VLITE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML
Emulsified Water	scalar	Visual*	>0.6	<b>NEG</b>	NEG
Free Water	scalar	Visual*		<b>NEG</b>	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	49.4	<b>49.1</b>	49.0

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : PP **Received** : 09 Jul 2024  
**Lab Number** : 02646716 **Tested** : 12 Jul 2024  
**Unique Number** : 5812268 **Diagnosed** : 12 Jul 2024 - Kevin Marson  
**Test Package** : IND 2 ( Additional Tests: KF )

**MOLSON TORONTO**  
 1 CARLINGVIEW DRIVE  
 TORONTO, ON  
 CA M9W 5E5  
 Contact: Heath Bagby  
 heath.bagby@molsoncoors.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.