

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id **100-050** Component Left Final Drive Fluid SAE 80W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0932559		
Sample Date		Client Info		20 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	۷	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	223		
Chromium	ppm	ASTM D5185(m)	>10	2		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	1		
Lead	ppm	ASTM D5185(m)	>25	0		
Copper	ppm	ASTM D5185(m)	>50	<1		
Tin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	200	<1		
Barium	ppm	ASTM D5185(m)	0	3		
Molybdenum	ppm	ASTM D5185(m)	0	<1		
Manganese	ppm	ASTM D5185(m)		3		
Magnesium	ppm	ASTM D5185(m)	0	2		
Calcium	ppm	ASTM D5185(m)	20	8		
Phosphorus	ppm	ASTM D5185(m)	1000	232		
Zinc	ppm	ASTM D5185(m)	20	11		
Sulfur	ppm	ASTM D5185(m)	22000	13792		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	9		
Sodium	ppm	ASTM D5185(m)	>50	1		
Potassium	ppm	ASTM D5185(m)	>20	2		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar	Visual*	NONE	LIGHT			
	Yellow Metal	scalar	Visual*	NONE	NONE			
	Precipitate	scalar	Visual*	NONE	NONE			
	Silt	scalar	Visual*	NONE	LIGHT			
	Debris	scalar	Visual*	NONE	NONE			
	Sand/Dirt	scalar	Visual*	NONE	NONE			
- 1/2	Appearance	scalar	Visual*	NORML	NORML			
Jun20/24	Odor	scalar	Visual*	NORML	NORML			
	Emulsified Water	scalar	Visual*	>0.2	NEG			
	Free Water	scalar	Visual*		NEG			
	FLUID PROPER	TIES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D7279(m)	135	176			
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2	
	Color					no image	no image	
	Bottom					no image	no image	
	GRAPHS							
	Iron (ppm)				Lead (ppm)			
	2000 Severe			150	Severe			
	5. 1000 - ⁷			E 100	- 0			
	Abnormal			50 0	0			
	Jun20/24			Jun20/24	Jun20/24		Jun20/24	
	·			Πηγ	-		ηn	
	Aluminum (ppm)			30	Chromium (p	om)		
	Severe				00000			
	a 100 Abnormal			²⁰ 10	Abnormal			
	0						4	
	Jun20/24			Jun20/24	Jun20/24		Jun20/24	
				ηη			'nſ	
	Copper (ppm)			300	Silicon (ppm)			
	Severe				0			
	Abnormal			툴 ²⁰⁰	Abnormal			
	0			- 0			4	
	Jun20/24			Jun20/24	Jun20/24		Jun20/24	
				ηn			n	
	Viscosity @ 40°C			300	Additives			
					6			
	Co 0 ⊕ 150 + Base Abnormal Abnormal			트 ²⁰⁰ 된 100	- zinc	s		
	100				4		4	
	Jun20/24			Jun20/24	Jun20/24		Jun20/24	
	بار			Ļ	Ϋ́,		Ju	
Laboratory	: WearCheck - C8-117				5H9 RONI/IR		CAVATING LTD.	
Sample No. Lab Number	: WC0932559 : 02647176	Rece Teste) Jul 2024) Jul 2024			VAUGHAN, ON	
Unique Number			-) Jul 2024 - W	es Davis		CA L4K 4P3	
Test Package	: MOBCE Contact: Service Team							
	contact Customer Serv						team@roni ca	

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

T: F: Contact/Location: Service Team - RONVAU



CALA

ISO 17025:2017 Accredited Laboratory

Page 2 of 2

service.team@roni.ca