OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
System 71 - Main Power Generation
Machine Id
Z-7101A Hydraulic Start Oil Train A
Component
Hydraulic System
Fluid
IRVING HYDRAULIC OIL LP 32 (290 LTR)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. The system and fluid cleanliness is acceptable.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PP**	PP	PP
Sample Date		Client Info		**02 Jul 2024**	13 Apr 2024	10 Dec 2023
Machine Age	hrs	Client Info		**0**	0	0
Oil Age	hrs	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**NORMAL**	NORMAL	NORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>20	**<1**	0	0
Chromium	ppm	ASTM D5185(m)	>10	**0**	0	0
Nickel	ppm	ASTM D5185(m)	>10	**<1**	0	<1
Titanium	ppm	ASTM D5185(m)		**0**	0	0
Silver	ppm	ASTM D5185(m)		**<1**	0	<1
Aluminum	ppm	ASTM D5185(m)	>10	**0**	0	0
Lead	ppm	ASTM D5185(m)	>20	**0**	5	2
Copper	ppm	ASTM D5185(m)	>20	**<1**	<1	<1
Tin	ppm	ASTM D5185(m)	>10	**0**	0	0
Antimony	ppm	ASTM D5185(m)		**0**	0	0
Vanadium	ppm	ASTM D5185(m)		**0**	0	0
Beryllium	ppm	ASTM D5185(m)		**0**	0	0
Cadmium	ppm	ASTM D5185(m)		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		**0**	<1	<1
Barium	ppm	ASTM D5185(m)		**0**	0	<1
Molybdenum	ppm	ASTM D5185(m)		**0**	0	0
Manganese	ppm	ASTM D5185(m)		**0**	0	0
Magnesium	ppm	ASTM D5185(m)		**<1**	<1	0
Calcium	ppm	ASTM D5185(m)		**36**	35	38
Phosphorus	ppm	ASTM D5185(m)		**179**	170	185
Zinc	ppm	ASTM D5185(m)	400	**133**	126	150
Sulfur	ppm	ASTM D5185(m)		**1919**	1975	1967
Lithium	ppm	ASTM D5185(m)		**<1**	<1	<1

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	**0**	<1	<1
Sodium	ppm	ASTM D5185(m)		**<1**	<1	<1
Potassium	ppm	ASTM D5185(m)	>20	**<1**	<1	0
Water	%	ASTM D6304*	>0.05	**0.003**	0.002	0.003
ppm Water	ppm	ASTM D6304*	>500	**32**	21	34

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	**2643**	721	904
Particles >6µm		ASTM D7647	>1300	**547**	157	230
Particles >14µm		ASTM D7647	>160	**27**	15	18
Particles >21µm		ASTM D7647	>40	**7**	6	5
Particles >38µm		ASTM D7647	>10	**1**	1	1
Particles >71µm		ASTM D7647	>3	**0**	1	1
Oil Cleanliness		ISO 4406 (c)	>19/17/14	**19/16/12**	17/14/11	17/15/11

OIL ANALYSIS REPORT

Water (KF)



Particle Trend



Water (KF)



Viscosity @ 40°C



Particle Trend



FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		**0.25**	0.26	0.30

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	**NONE**	NONE	NONE
Precipitate	scalar	Visual*	NONE	**NONE**	NONE	NONE
Silt	scalar	Visual*	NONE	**NONE**	NONE	NONE
Debris	scalar	Visual*	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	**NONE**	NONE	NONE
Appearance	scalar	Visual*	NORML	**NORML**	NORML	NORML
Odor	scalar	Visual*	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	Visual*	>0.05	**NEG**	NEG	NEG
Free Water	scalar	Visual*		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	31.9	**31.4**	31.1	31.6

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					



GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number



ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PP
Lab Number : 02648699
Unique Number : 5814251
Test Package : MAR 2 (Additional Tests: KF)

Received : 18 Jul 2024
Tested : 19 Jul 2024
Diagnosed : 19 Jul 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

HIBERNIA MGMT & DEVELOPMENT CO. LTD
SUITE 1000,, 100 NEW GOWER STREET
ST.JOHNS, NL
CA A1C 6K3
Contact: Sam Nash
samantha.m.nash@exxonmobil.com
T:
F: (709)722-3766