

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Machine Id

HITACHI HITACHI ZW220-SB

Component Hydraulic System Fluid

{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. Please contact your representative for information regarding the proper sampling kits for your service. NOTE: We recommend using MOB 2 test kits, this testkit includes Particle Count to determine the ISO cleanliness of the fluid.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component(unconfirmed).


Fluid Condition

The condition of the oil is acceptable for the time in service.

B								
						\checkmark		
		<u>[</u>		Jul2024				
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		WC0967066				
Sample Date		Client Info		17 Jul 2024				
Machine Age	hrs	Client Info		7689				
Dil Age	hrs	Client Info		0				
Oil Changed		Client Info		N/A				
Sample Status				NORMAL				
CONTAMINATION		method	limit/base	current	history1	history2		
Nater		WC Method	>0.1	NEG				
WEAR METALS		method	limit/base	current	history1	history2		
ron	ppm	ASTM D5185(m)	>20	13				
Chromium	ppm	ASTM D5185(m)	>10	0				
Nickel	ppm	ASTM D5185(m)	>10	<1				
Fitanium	ppm	ASTM D5185(m)		0				
Silver	ppm	ASTM D5185(m)		0				
Aluminum	ppm	ASTM D5185(m)	>10	3				
_ead	ppm	ASTM D5185(m)	>10	<1				
Copper	ppm	ASTM D5185(m)	>75	2				
Tin	ppm	ASTM D5185(m)	>10	0				
Antimony	ppm	ASTM D5185(m)		0				
/anadium	ppm	ASTM D5185(m)		0				
Beryllium	ppm	ASTM D5185(m)		0				
Cadmium	ppm	ASTM D5185(m)		0				
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185(m)		0				
Barium	ppm	ASTM D5185(m)		0				
Nolybdenum	ppm	ASTM D5185(m)		0				
Manganese	ppm	ASTM D5185(m)		<1				
Magnesium	ppm	ASTM D5185(m)		5				
Calcium	ppm	ASTM D5185(m)		24				
Phosphorus	ppm	ASTM D5185(m)		314				
Zinc	ppm	ASTM D5185(m)		61				
Sulfur	ppm	ASTM D5185(m)		1556				
Lithium	ppm	ASTM D5185(m)		<1				
CONTAMINANTS		method	limit/base	current	history1	history2		
	ppm	ASTM D5185(m)	>20	4				
Silicon	ppiii							
Silicon Sodium	ppm	ASTM D5185(m)		<1				



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
1	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
	Precipitate	scalar	Visual*	NONE	NONE		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
Jul17/24	Appearance	scalar	Visual*	NORML	NORML		
<u>ب</u>	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.1	NEG		
	Free Water	scalar	Visual*		NEG		
	FLUID PROPERT		method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D7279(m)		44.7		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
	Color					no image	no image
	Bottom					no image	no image
	GRAPHS						
	Iron (ppm)				Lead (ppm)		
	40 Severe			30			
	E 20 - Abnormal			²⁰ ق	Abnormal		
	Jul17/24			Jul17/24	Jul17/24		
	∼ Aluminum (ppm)			7	Chromium (pp	(m)	
	³⁰ Severe			30			
	= 20			²⁰ 10			
	and the second s				Abnormal		
	0440			0	724		
	Jul17/24			Jul17/24	Jul17/24		
	Copper (ppm)				Silicon (ppm)		
	300 T			60	Severe		
	E 200 - G			특 ⁴⁰ 문 ₂₀	Abnormal		
	100 - Abnormal			0	ļ		
	Jul17/24			Jul17/24	Jull 7/24		
				Jul	-		
	Viscosity @ 40°C			400	Additives		
					calcium		****
	(2, 50 - Abnormal 영 40 - Abnormal			톱 200	zinc		
	30			0	24		
	Jul17/24			Jul17/24	Jul17/24		
Laboratory Sample No. Lab Number	: WearCheck - C8-117 : WC0967066 : 02648715	5 Appleby Recei	ived : 18	igton, ON L7L 3 Jul 2024 3 Jul 2024	. 5H9		T EQUIPMEN 1793 LINE 1 GILFORD, O

Validity of results and interpretation are based on the sample and information as supplied. Report Id: DEWGIL [WCAMIS] 02648715 (Generated: 07/18/2024 13:37:18) Rev: 1

Contact/Location: Matthew DeWitt - DEWGIL Page 2 of 2

F: