

OIL ANALYSIS REPORT

Sample Rating Trend





Compressor Fluid

KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
|------------------|---------------|----------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | KC94015 | | |
| Sample Date | | Client Info | | 28 Jan 2021 | | |
| Machine Age | hrs | Client Info | | 472 | | |
| Oil Age | hrs | Client Info | | 472 | | |
| Oil Changed | | Client Info | | Changed | | |
| Sample Status | | | | NORMAL | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >50 | <1 | | |
| Chromium | ppm | ASTM D5185m | >10 | 0 | | |
| Nickel | ppm | ASTM D5185m | >3 | 0 | | |
| Titanium | ppm | ASTM D5185m | >3 | 0 | | |
| Silver | ppm | ASTM D5185m | >2 | 0 | | |
| Aluminum | ppm | ASTM D5185m | >10 | 0 | | |
| _ead | ppm | ASTM D5185m | >10 | <1 | | |
| Copper | ppm | ASTM D5185m | | <1 | | |
| Tin | ppm | ASTM D5185m | >10 | 0 | | |
| Antimony | ppm | ASTM D5185m | | 0 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | | ASTM D5185m | | 0 | | |
| | ppm | | 11 14 1 | | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 0 | 0 | | |
| Barium | ppm | ASTM D5185m | 90 | 15 | | |
| Volybdenum | ppm | ASTM D5185m | 0 | 0 | | |
| Vanganese | ppm | ASTM D5185m | | <1 | | |
| Magnesium | ppm | ASTM D5185m | 100 | 65 | | |
| Calcium | ppm | ASTM D5185m | 0 | <1 | | |
| Phosphorus | ppm | ASTM D5185m | 0 | 6 | | |
| Zinc | ppm | ASTM D5185m | 0 | 0 | | |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 0 | | |
| Sodium | ppm | ASTM D5185m | | 8 | | |
| Potassium | ppm | ASTM D5185m | >20 | 27 | | |
| Water | % | ASTM D6304 | >0.05 | 0.012 | | |
| opm Water | ppm | ASTM D6304 | >500 | 123.2 | | |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | | 4565 | | |
| Particles >6µm | | ASTM D7647 | >1300 | 769 | | |
| Particles >14µm | | ASTM D7647 | >80 | 8 | | |
| Particles >21µm | | ASTM D7647 | | 2 | | |
| Particles >38µm | | ASTM D7647 | >4 | 0 | | |
| Particles >71µm | | ASTM D7647 | | 0 | | |
| Oil Cleanliness | | ISO 4406 (c) | >/17/13 | 17/10 | | |
| FLUID DEGRADA | TION_ | method | limit/base | current | history1 | history2 |
| | mg KOH/g | ASTM D8045 | 1.0 | 0.262 | | |
| Acid Number (AN) | iiiy N∪⊓/g | 70 I IVI D0040 | 1.0 | 0.202 | | |



OIL ANALYSIS REPORT







* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: