

GREASE ANALYSIS

Sample Rating Trend

NORMAL

Area DAKOTA RANGE III [200006928] Machine Id 13WEA87751 - C-02 Component

Front Grease

MOBIL SHC GREASE 460 WT (--- LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Grease Condition

The condition of the greases additive package is suitable for further service.

Contaminants


Insufficient sample was received to conduct all the routine laboratory tests. There is no indication of any contamination in the grease.

| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|------------|-------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | NX05576094 | | |
| Sample Date | | Client Info | | 02 Mar 2022 | | |
| Machine Age | hrs | Client Info | | 4483 | | |
| Grease Age | hrs | Client Info | | 0 | | |
| Grease Serviced | | Client Info | | N/A | | |
| Sample Status | | | | NORMAL | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >250 | 293 | | |
| Chromium | ppm | ASTM D5185m | >10 | 2 | | |
| Nickel | ppm | ASTM D5185m | >5 | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| Titanium | ppm | ASTM D5185m | | <1 | | |
| Vanadium | ppm | ASTM D5185m | | <1 | | |
| Lead | ppm | ASTM D5185m | >25 | 2 | | |
| Copper | ppm | ASTM D5185m | >75 | 122 | | |
| Tin | ppm | ASTM D5185m | >5 | <1 | | |
| Silver | ppm | ASTM D5185m | >5 | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 107 | | |
| Magnesium | ppm | ASTM D5185m | | 1 | | |
| Manganese | ppm | ASTM D5185m | | 5 | | |
| Molybdenum | ppm | ASTM D5185m | | 555 | | |
| Phosphorus | ppm | ASTM D5185m | | 85 | | |
| Zinc | ppm | ASTM D5185m | | 114 | | |
| THICKENER/SOA | ۱P | method | limit/base | current | history1 | history2 |
| Aluminum | ppm | ASTM D5185m | | 6 | | |
| Barium | ppm | ASTM D5185m | | 2 | | |
| Calcium | ppm | ASTM D5185m | | 31 | | |
| Sodium | ppm | ASTM D5185m | | 20 | | |
| Lithium | ppm | ASTM D5185m | | 2981 | | |
| Sulfur | ppm | ASTM D5185m | | 3283 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >150 | 24 | | |
| Potassium | ppm | ASTM D5185m | | 2 | | |
| GREASE CONDI | ΓΙΟΝ | method | limit/base | current | history1 | history2 |
| Grease Color | | *Visual | Red | Red | | |
| Texture | | *In-house | | Buttery | | |
| NLGI Consistency | NLGI Scale | *SKF Method | 1.5 | 2 | | |
| | | | | - | | |



GREASE ANALYSIS

| Bottom no image no image PrtFilter no image no image no image GRAPHS Ferrous Alloys 0 0 0 0 0 0 0 0 0 0 0 0 0 | SAMPLE IMAGES | method | limit/base | current | history1 | history |
|--|----------------------|--------|------------|----------|----------|----------|
| PrtFilter no image no image no image | Color | | | | no image | no image |
| GRAPHS Ferrous Alloys | Bottom | | | | no image | no image |
| Ferrous Alloys | PrtFilter | | | no image | no image | no image |
| Ferrous Alloys | GRAPHS | | | | | |
| Non-ferrous Metals | Ferrous Alloys | | | | | |
| Non-ferrous Metals | ¹⁰ T | | | | | |
| Non-ferrous Metals | | | | | | |
| Non-ferrous Metals | | | | | | |
| Non-ferrous Metals | 50 | | | | | |
| Non-ferrous Metals | 00- | | | | | |
| Non-ferrous Metals | 50 - | | | | | |
| Non-ferrous Metals | | | | | | |
| Non-ferrous Metals | r2/22 | | r2/22 - | | | |
| Copper copper image: Sead image: Sead im | | | Ma | | | |
| | Non-ferrous Metals | | | | | |
| | | | | | | |
| | 00 | | | | | |
| | 80 | | | | | |
| | | | | | | |
| 0 | | | | | | |
| iat 2.22 | 50 | | | | | |
| lar2/21 | 30 - 10 - | | | | | |
| | 50 - 10 - 20 - | | | | | |



Contact/Location: DEVIN LINEHAN - NORDEX