

PROBLEM SUMMARY

Machine Id **49262091 (S/N 13336)** Component

Hydraulic System Fluid MOBIL DTE 24 (--- GAL)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS										
Sample Status		ABNORMAL								
Copper	ppm	ASTM D5185m	>20	<u> </u>						


Customer Id: TECGRENC Sample No.: WC0731069 Lab Number: 05651448 Test Package: PLANT



To manage this report scan the QR code

To discuss the diagnosis or test data: Angela Borella +1 800-237-1369 angela.borella@wearcheckusa.com

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com



There are no recommended actions for this sample.

HISTORICAL DIAGNOSIS



OIL ANALYSIS REPORT

Sample Rating Trend

WEAR

Machine Id 49262091 (S/N 13336) Component

Hydraulic System Fluid MOBIL DTE 24 (--- GAL)

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

🔺 Wear

The copper level is abnormal. All other component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0731069		
Sample Date		Client Info		26 Sep 2022		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				ABNORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	9		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>20	<1		
Lead	ppm	ASTM D5185m	>20	15		
Copper	ppm	ASTM D5185m	>20	<u> </u>		
Tin	ppm	ASTM D5185m	>20	4		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2		
Barium	ppm	ASTM D5185m		3		
Molybdenum	ppm	ASTM D5185m		3		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		17		
Calcium	ppm	ASTM D5185m		191		
Phosphorus	ppm	ASTM D5185m		476		
Zinc	ppm	ASTM D5185m		704		
Sulfur	ppm	ASTM D5185m		5405		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	2373		
Particles >6µm		ASTM D7647	>1300	198		
Particles >14µm		ASTM D7647	>160	4		
Particles >21µm		ASTM D7647	>40	1		
Particles >38µm		ASTM D7647	>10	0		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/15/9		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.74		



OIL ANALYSIS REPORT



Contact/Location: BILLIE WALLACE - TECGRENC

T:

F:

4406

:1999 Cle

14