




# PROBLEM SUMMARY

Sample Rating Trend



WEAR




Machine Id  
**48945607 (S/N 11976)**

Component  
**Hydraulic System**

Fluid  
**MOBIL DTE 24 (--- GAL)**

## COMPONENT CONDITION SUMMARY

### ▲ Non-ferrous Metals



## RECOMMENDATION

No corrective action is recommended at this time.  
Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status	ABNORMAL	---	---
Copper	ppm	ASTM D5185m	>20
	▲ 24	---	---

Customer Id: TECGRENC  
Sample No.: WC0731074  
Lab Number: 05651456  
Test Package: PLANT



To manage this report scan the QR code

To discuss the diagnosis or test data:  
Angela Borella +1 800-237-1369  
[angela.borella@wearcheckusa.com](mailto:angela.borella@wearcheckusa.com)

To change component or sample information:  
Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

*There are no recommended actions for this sample.*

## HISTORICAL DIAGNOSIS



# OIL ANALYSIS REPORT

Sample Rating Trend


**WEAR**



Machine Id  
**48945607 (S/N 11976)**

Component  
**Hydraulic System**

Fluid  
**MOBIL DTE 24 (--- GAL)**



## DIAGNOSIS

### ▲ Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

### ▲ Wear

The copper level is abnormal. All other component wear rates are normal.

### Contamination

The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>WC0731074</b>	---	---
Sample Date	Client Info	<b>26 Sep 2022</b>	---	---
Machine Age	hrs Client Info	<b>0</b>	---	---
Oil Age	hrs Client Info	<b>0</b>	---	---
Oil Changed	Client Info	<b>N/A</b>	---	---
Sample Status		<b>ABNORMAL</b>	---	---

## WEAR METALS

method	limit/base	current	history1	history2
Iron ppm ASTM D5185m	>20	<b>18</b>	---	---
Chromium ppm ASTM D5185m	>20	<b>0</b>	---	---
Nickel ppm ASTM D5185m	>20	<b>0</b>	---	---
Titanium ppm ASTM D5185m		<b>0</b>	---	---
Silver ppm ASTM D5185m		<b>0</b>	---	---
Aluminum ppm ASTM D5185m	>20	<b>&lt;1</b>	---	---
Lead ppm ASTM D5185m	>20	<b>7</b>	---	---
Copper ppm ASTM D5185m	>20	<b>▲ 24</b>	---	---
Tin ppm ASTM D5185m	>20	<b>2</b>	---	---
Vanadium ppm ASTM D5185m		<b>0</b>	---	---
Cadmium ppm ASTM D5185m		<b>0</b>	---	---

## ADDITIVES

method	limit/base	current	history1	history2
Boron ppm ASTM D5185m		<b>1</b>	---	---
Barium ppm ASTM D5185m		<b>2</b>	---	---
Molybdenum ppm ASTM D5185m		<b>&lt;1</b>	---	---
Manganese ppm ASTM D5185m		<b>&lt;1</b>	---	---
Magnesium ppm ASTM D5185m		<b>56</b>	---	---
Calcium ppm ASTM D5185m		<b>77</b>	---	---
Phosphorus ppm ASTM D5185m		<b>351</b>	---	---
Zinc ppm ASTM D5185m		<b>458</b>	---	---
Sulfur ppm ASTM D5185m		<b>1787</b>	---	---

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon ppm ASTM D5185m	>15	<b>2</b>	---	---
Sodium ppm ASTM D5185m		<b>0</b>	---	---
Potassium ppm ASTM D5185m	>20	<b>1</b>	---	---

## FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm ASTM D7647	>5000	<b>2529</b>	---	---
Particles >6µm ASTM D7647	>1300	<b>177</b>	---	---
Particles >14µm ASTM D7647	>160	<b>5</b>	---	---
Particles >21µm ASTM D7647	>40	<b>1</b>	---	---
Particles >38µm ASTM D7647	>10	<b>1</b>	---	---
Particles >71µm ASTM D7647	>3	<b>0</b>	---	---
Oil Cleanliness ISO 4406 (c)	>19/17/14	<b>19/15/10</b>	---	---

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN) mg KOH/g ASTM D8045		<b>0.40</b>	---	---




# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.05	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	31.5	34.0	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0731074 **Received** : 27 Sep 2022  
**Lab Number** : 05651456 **Diagnosed** : 28 Sep 2022  
**Unique Number** : 10151008 **Diagnostician** : Angela Borella  
**Test Package** : PLANT

**TE CONNECTIVITY**  
 719 PEGG RD  
 GREENSBORO, NC  
 US 27409  
 Contact: BILLIE WALLACE  
 billie.wallace@te.com

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)