

OIL ANALYSIS REPORT

Sample Rating Trend

ISO



KAESER 7295658

Component

Compressor

KAESER SIGMA (OEM) S-460 (--- QTS)

▲ Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| | | | | Nov2022 | | |
|----------------------------|--------|--------------|------------|------------------|----------|----------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | KCP46408 | | |
| Sample Date | | Client Info | | 16 Nov 2022 | | |
| Machine Age | hrs | Client Info | | 7594 | | |
| Oil Age | hrs | Client Info | | 1777 | | |
| Oil Changed | | Client Info | | Not Changd | | |
| Sample Status | | | | ATTENTION | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >50 | 0 | | |
| Chromium | ppm | ASTM D5185m | >10 | 0 | | |
| Nickel | ppm | ASTM D5185m | >3 | <1 | | |
| Titanium | ppm | ASTM D5185m | >3 | 0 | | |
| Silver | ppm | ASTM D5185m | >2 | 0 | | |
| Aluminum | ppm | ASTM D5185m | >10 | <1 | | |
| Lead | ppm | ASTM D5185m | >10 | <1 | | |
| Copper | ppm | ASTM D5185m | >50 | 2 | | |
| Tin | ppm | ASTM D5185m | >10 | <1 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | | |
| Barium | ppm | ASTM D5185m | 90 | 15 | | |
| Molybdenum | ppm | ASTM D5185m | | 0 | | |
| Manganese | ppm | ASTM D5185m | | 0 | | |
| Magnesium | ppm | ASTM D5185m | 90 | 77 | | |
| Calcium | ppm | ASTM D5185m | 2 | 2 | | |
| Phosphorus | ppm | ASTM D5185m | | 7 | | |
| Zinc | ppm | ASTM D5185m | | 2 | | |
| Sulfur | ppm | ASTM D5185m | | 21724 | | |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 1 | | |
| Sodium | ppm | ASTM D5185m | | 22 | | |
| Potassium | ppm | ASTM D5185m | >20 | 8 | | |
| Water | % | ASTM D6304 | >0.05 | 0.024 | | |
| ppm Water | ppm | ASTM D6304 | >500 | 246.9 | | |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | | 15011 | | |
| Particles >6µm | | ASTM D7647 | >1300 | 2075 | | |
| Particles >14µm | | ASTM D7647 | >80 | 67 | | |
| Particles >21µm | | ASTM D7647 | >20 | 13 | | |
| Particles >38μm | | ASTM D7647 | >4 | 1 | | |
| Particles >71μm | | ASTM D7647 | >3 | 0 | | |
| Oil Cleanliness | | ISO 4406 (c) | >/17/13 | 2 1/18/13 | | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| A atal Nicosala a v. (ANI) | | 4.OTM D00.45 | 0.4 | 0.22 | | |


Acid Number (AN)

mg KOH/g ASTM D8045 0.4

0.33



OIL ANALYSIS REPORT



Contact/Location: BOB KIPP - AMASTN