

## **OIL ANALYSIS REPORT**

#### Sample Rating Trend



### A103 (S/N 6409-11) Component

### Wind Turbine Gearbox

MOBIL MOBILGEAR SHC XMP 320 (74 GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





#### arž011 Nov2014 Aug2016 Feb2018 Nov2018 Sep2019 Oct2021

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		MHI025361	MHI018312	MHI019241
Sample Date		Client Info		26 Oct 2022	28 Oct 2021	23 Oct 2020
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		90190	84477	78183
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184	>200	10	17	19
Iron	ppm	ASTM D5185m	>200	3	3	6
Chromium	ppm	ASTM D5185m	>3	0	0	0
Nickel	ppm	ASTM D5185m	>3	1	0	0
Titanium	ppm	ASTM D5185m	>10	0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	0	0	0
Lead	ppm	ASTM D5185m	>15	<1	0	0
Copper	ppm	ASTM D5185m	>75	5	9	4
Tin	ppm	ASTM D5185m	>10	0	0	0
Antimony	ppm	ASTM D5185m	>5		0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		<1	0	0
Calcium	ppm	ASTM D5185m	0	<1	0	0
Phosphorus	ppm	ASTM D5185m	485	386	398	371
Zinc	ppm	ASTM D5185m	0	10	10	10
Sulfur	ppm	ASTM D5185m		4927	3402	3605
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+30	<1	0	<1
Sodium	ppm	ASTM D5185m	>15	<1	0	0
Potassium	ppm	ASTM D5185m	>20	2	0	0
Water	%	ASTM D6304	>0.1	0.008	0.011	0.001
ppm Water	ppm	ASTM D6304	>1000	87.3	110.9	14.6
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		327	354	17255
Particles >6µm		ASTM D7647	>5000	77	74	1546
Particles >14µm		ASTM D7647	>640	12	8	68
Particles >21µm		ASTM D7647	>160	3	2	20
Particles >38µm		ASTM D7647	>40	0	0	2
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/19/16	16/13/11	16/13/10	21/18/13




# **OIL ANALYSIS REPORT**


Color


Bottom

12000	Water	(KF)	)					F
10000	Severe							Aci
Ê 8000								V
Vater (ppm)								
≥ 4000								Wh
2000	Abnorma							Ye
0	Contentina							_ Pre
	Apr4/11	Nov18/14	Aug25/16 -	Feb9/18	Nov5/18	Sep26/19	0ct28/21	Silt
	Ap	Nov	Augi	Fel	Nor	Sep.	Oct	De
	PQ							Sa
400	T S S S S S S							Ар
350	Severe							Od
300								Em
250 문200-	Abnorma							Fre
150	1							
100								F
50								Vis
0		4	9			6	21-	
	Apr4//	Nov18/14	Aug25/16	Feb9/18 -	Nov5/18 -	Sep26/19	0ct28/21	S



FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	1.10	1.073	0.908
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	335	356	359	357
SAMPLE IMAGES		method	limit/base	current	history1	history2
				and the second division of the second divisio		





Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)