

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **35147** Component **Diesel Engine** Fluid **DIESEL ENGINE OIL SAE 40 (--- QTS)**

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KLM2339298		
Sample Date		Client Info		12 Feb 2023		
Machine Age	mls	Client Info		154402		
Oil Age	mls	Client Info		53977		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	11		
Chromium	ppm	ASTM D5185m	>20	2		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	4		
Lead	ppm	ASTM D5185m	>40	<1		
Copper	ppm	ASTM D5185m	>330	5		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	43		
Barium	ppm	ASTM D5185m	10	0		
Molybdenum	ppm	ASTM D5185m	100	49		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m	450	896		
Calcium	ppm	ASTM D5185m	3000	1348		
Phosphorus	ppm	ASTM D5185m	1150	970		
Zinc	ppm	ASTM D5185m	1350	1313		
Sulfur	ppm	ASTM D5185m	4250	3867		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m	>216	4		
Potassium	ppm	ASTM D5185m	>20	7		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.4		
Nitration	Abs/cm	*ASTM D7624	>20	8.1		
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.7		





OIL ANALYSIS REPORT

Particle Trend










 $\overline{\mu}$

	IESS	method	limit/base	current	history1	history
Particles >4µm		ASTM D7647		948		
Particles >6µm		ASTM D7647	>5000	517		
Particles >14µm		ASTM D7647	>640	88		
Particles >21µm		ASTM D7647	>160	30		
Particles >38µm		ASTM D7647	>40	5		
Particles >71µm		ASTM D7647	>10	0		
Oil Cleanliness		ISO 4406 (c)	>19/16	16/14		
FLUID DEGRADA	TION	method	limit/base	current	history1	history
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6		
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	10.32		
VISUAL		method	limit/base	current	history1	history
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual	20.L	NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history
Visc @ 100°C	cSt	ASTM D445	14.4	13.8		
GRAPHS						
Ferrous Alloys				Particle Count		
5			491,520			
			491,520			
0 iron						
0 5 5 5 6 0			122,880 - 30,720 -	· · · ·		
0 5 5 5 6 0			122,880 - 30,720 -		•	
iron chromium nickel			122,880 - 30,720 -			
ESZ 21 Non-ferrous Metal	s		122,880 - 30,720 -			
iron chromium nickel	s		122,880 - 30,720 -			
Non-ferrous Metal	5		122,880 30,720 E 7,680 E 7,680 E 1,920 B 1,920			
Non-ferrous Metal	5		122,880 30,720 2			
Non-ferrous Metal	s		122,880 30,720 20,720 20,227 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777	Beresemal		
Non-ferrous Metal	s		122,880 30,720 20,720 20,227 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777 20,2777	Beresemal		
Non-ferrous Metal	_		122,880 30,720 2	Sbreaemal	144 214	
Non-ferrous Metal	_		122,880 30,720 20,720 20,00000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,00000 20,0000 20,00000000	Base Number	14μ 21μ	
Non-ferrous Metal	_		122,880 30,720 20,720 20,00000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,0000 20,00000 20,0000 20,00000000	л 6µ	14μ 21μ	
Non-ferrous Metal	_		122,880 30,720 TE 7,680 EC771(9) 990 990 990 990 990 990 990 990 990 9	Base Number	14μ 21μ	
Non-ferrous Metal	_		122,880 30,720 TE 7,680 EC771(9) 990 990 990 990 990 990 990 990 990 9	Base Number	14μ 21μ	
Non-ferrous Metal	_		122,880 30,720 7,680 52721(9) 9 9 9 9 9 9 9 9 9 9 9 9 9 9 9 9 9 9	Base Number	14μ 21μ	



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: CLYDE OMIJA - CITAIE