

PROBLEM SUMMARY





X

KMGP UNIT 2

Component Inboard Bearing Fluid ROYAL PURPLE SYNFILM GT 32 (--- GAL)

COMPONENT CONDITION SUMMARY

	6 160 -	Non-ferrous Metals	
	140	copper"	ļ.
	120	readu readu	
	100		i T =
ppm	80		
	60		
	40		ł
	20-		t
	01	Feb16/23 -	reb b/23 -

RECOMMENDATION

We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

PROBLEMATIC 1	PROBLEMATIC TEST RESULTS							
Sample Status				SEVERE				
Lead	ppm	ASTM D5185m	>20	🛑 150				
Copper	ppm	ASTM D5185m	>20	4 9				
Tin	ppm	ASTM D5185m	>20	<u> </u>				

Customer Id: MAGHOU Sample No.: RP0028244 Lab Number: 05797617 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Doug Bogart +1 (800)237-1369 x4016 <u>dougb@wearcheckusa.com</u>

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED AC	ECOMMENDED ACTIONS					
Action	Status	tatus Date Done By		Description		
Inspect Wear Source			?	We advise that you inspect for the source(s) of wear.		
Resample			?	We recommend an early resample to monitor this condition.		

HISTORICAL DIAGNOSIS



OIL ANALYSIS REPORT

Sample Rating Trend

WEAR

KMGP UNIT 2

Inboard Bearing

ROYAL PURPLE SYNFILM GT 32 (--- GAL)

DIAGNOSIS

Recommendation

We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

🛡 Wear

Bearing and/or bushing wear is indicated.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid.

			Provide de	Feb 2023	1.1	
SAMPLE INFORM	VIATION	method	limit/base	current	history1	history2
Sample Number		Client Info		RP0028244		
Sample Date		Client Info		16 Feb 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				SEVERE		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>20	<1		
Lead	ppm	ASTM D5185m	>20	• 150		
Copper	ppm	ASTM D5185m	>20	4 9		
Tin	ppm	ASTM D5185m	>20	A 34		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum		ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		55		
Calcium	ppm	ASTM D5185m		4		
	ppm	ASTM D5185m		4		
Phosphorus Zinc	ppm	ASTM D5185m		11		
-	ppm	ASTIM DOTODIII		11		
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	14		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304	>2	0.010		
ppm Water	ppm	ASTM D6304		101.8		
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.41		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	LIGHT		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	VLITE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>2	NEG		
Free Water	scalar	*Visual		NEG	tion: LOGAN S	EYLMAGHOU



OIL ANALYSIS REPORT



Contact/Location: LOGAN SEYL - MAGHOU