


# **OIL ANALYSIS REPORT**

WHEY SL23AG21

Component Gearbox

MOBIL SHC 630 (--- GAL)





#### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

#### Wear

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the


## **Fluid Condition**

The condition of the oil is acceptable for the time in service.

|                         |        | May/2016 May/2019 May/2021 Apr/2023 |            |             |             |             |  |
|-------------------------|--------|-------------------------------------|------------|-------------|-------------|-------------|--|
| SAMPLE INFORM           | MATION | method                              | limit/base | current     | history1    | history2    |  |
| Sample Number           |        | Client Info                         |            | WC0797224   | WC0579331   | WC04712512  |  |
| Sample Date             |        | Client Info                         |            | 21 Apr 2023 | 29 May 2021 | 03 May 2019 |  |
| Machine Age             | hrs    | Client Info                         |            | 0           | 0           | 0           |  |
| Oil Age                 | hrs    | Client Info                         |            | 0           | 0           | 0           |  |
| Oil Changed             |        | Client Info                         |            | N/A         | N/A         | N/A         |  |
| Sample Status           |        |                                     |            | NORMAL      | NORMAL      | NORMAL      |  |
| WEAR METALS             |        | method                              | limit/base | current     | history1    | history2    |  |
| Iron                    | ppm    | ASTM D5185m                         | >200       | 87          | 70          | 102         |  |
| Chromium                | ppm    | ASTM D5185m                         | >15        | <1          | <1          | 1           |  |
| Nickel                  | ppm    | ASTM D5185m                         | >15        | 0           | <1          | <1          |  |
| Titanium                | ppm    | ASTM D5185m                         |            | 0           | <1          | 0           |  |
| Silver                  | ppm    | ASTM D5185m                         |            | 0           | 0           | 0           |  |
| Aluminum                | ppm    | ASTM D5185m                         | >25        | 1           | 0           | 2           |  |
| Lead                    | ppm    | ASTM D5185m                         | >100       | 0           | 7           | 0           |  |
| Copper                  | ppm    | ASTM D5185m                         | >200       | 0           | 4           | 0           |  |
| Tin                     | ppm    | ASTM D5185m                         | >25        | 0           | <1          | 0           |  |
| Antimony                | ppm    | ASTM D5185m                         | >5         |             | 0           | 3           |  |
| Vanadium                | ppm    | ASTM D5185m                         |            | 0           | 0           | 0           |  |
| Cadmium                 | ppm    | ASTM D5185m                         |            | 0           | 0           | 0           |  |
| ADDITIVES               |        | method                              | limit/base | current     | history1    | history2    |  |
| Boron                   | ppm    | ASTM D5185m                         |            | 0           | 14          | <1          |  |
| Barium                  | ppm    | ASTM D5185m                         |            | 0           | 7           | 0           |  |
| Molybdenum              | ppm    | ASTM D5185m                         |            | 0           | <1          | 0           |  |
| Manganese               | ppm    | ASTM D5185m                         |            | <1          | <1          | <1          |  |
| Magnesium               | ppm    | ASTM D5185m                         |            | <1          | <1          | <1          |  |
| Calcium                 | ppm    | ASTM D5185m                         |            | 0           | 1           | 0           |  |
| Phosphorus              | ppm    | ASTM D5185m                         |            | 476         | 355         | 393         |  |
| Zinc                    | ppm    | ASTM D5185m                         |            | 4           | 11          | 9           |  |
| Sulfur                  | ppm    | ASTM D5185m                         |            | 274         | 7602        | 112         |  |
| CONTAMINANTS            | ;      | method                              | limit/base | current     | history1    | history2    |  |
| Silicon                 | ppm    | ASTM D5185m                         | >50        | 22          | 18          | 28          |  |
| Sodium                  | ppm    | ASTM D5185m                         |            | <1          | 1           | <1          |  |
| Potassium               | ppm    | ASTM D5185m                         | >20        | 0           | <1          | 16          |  |
| VISUAL                  |        | method                              | limit/base | current     | history1    | history2    |  |
| White Metal             | scalar | *Visual                             | NONE       | NONE        | NONE        | NONE        |  |
| Yellow Metal            | scalar | *Visual                             | NONE       | NONE        | NONE        | NONE        |  |
| Precipitate             | scalar | *Visual                             | NONE       | NONE        | NONE        | NONE        |  |
| Silt                    | scalar | *Visual                             | NONE       | NONE        | MODER       | LIGHT       |  |
| Debris                  | scalar | *Visual                             | NONE       | NONE        | NONE        | NONE        |  |
| Sand/Dirt               | scalar | *Visual                             | NONE       | NONE        | NONE        | NONE        |  |
| Appearance              | scalar | *Visual                             | NORML      | NORML       | NORML       | NORML       |  |
| Odor                    | scalar | *Visual                             | NORML      | NORML       | NORML       | NORML       |  |
| <b>Emulsified Water</b> | scalar | *Visual                             | >0.2       | NEG         | NEG         | NEG         |  |
| Free Water              | scalar | *Visual                             |            | NEG         | NEG         | NEG         |  |
|                         |        |                                     |            |             |             |             |  |



# **OIL ANALYSIS REPORT**



| FLUID PROPERTIES |     | method    | limit/base | current | history1 | history2 |
|------------------|-----|-----------|------------|---------|----------|----------|
| Visc @ 40°C      | cSt | ASTM D445 | 217.7      | 219     | 212      | 215      |
| SAMPLE IMAGES    |     | method    | limit/base | current | history1 | history2 |
| Color            |     |           |            |         |          |          |
| Bottom           |     |           |            |         |          |          |

# **GRAPHS** Ferrous Alloys 120 Non-ferrous Metals Viscosity @ 40°C SS 210 55 210 22 210 200 190 180





Laboratory Sample No. Lab Number Unique Number : 10446820 Test Package : IND 1

: WC0797224 : 05833327

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 Apr 2023 Diagnosed : 01 May 2023 Diagnostician : Wes Davis

**LEPRINO FOODS-GREELEY** 1302 1ST AVE

GREELEY, CO US 80631-5909 Contact: ERIC KLINE

EKLINE@LEPRINOFOODS.COM

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (970)347-5190