

# **OIL ANALYSIS REPORT**

GTC 1200-85P

Component **Hydraulic System** 

SHELL TELLUS T32 (410 GAL)

# Sample Rating Trend



# Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

## Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.


# **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

|                  |          | L            | Mar2023    | May2023     |             |          |
|------------------|----------|--------------|------------|-------------|-------------|----------|
| SAMPLE INFORM    | MATION   | method       | limit/base | current     | history1    | history2 |
| Sample Number    |          | Client Info  |            | WC0752766   | WC0736493   |          |
| Sample Date      |          | Client Info  |            | 15 May 2023 | 29 Mar 2023 |          |
| Machine Age      | hrs      | Client Info  |            | 85          | 82          |          |
| Oil Age          | hrs      | Client Info  |            | 0           | 0           |          |
| Oil Changed      |          | Client Info  |            | Filtered    | Filtered    |          |
| Sample Status    |          |              |            | NORMAL      | NORMAL      |          |
| WEAR METALS      |          | method       | limit/base | current     | history1    | history2 |
| Iron             | ppm      | ASTM D5185m  | >20        | 0           | <1          |          |
| Chromium         | ppm      | ASTM D5185m  | >20        | 0           | 0           |          |
| Nickel           | ppm      | ASTM D5185m  | >20        | 0           | 0           |          |
| Titanium         | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Silver           | ppm      | ASTM D5185m  |            | 0           | <1          |          |
| Aluminum         | ppm      | ASTM D5185m  | >20        | 0           | 0           |          |
| Lead             | ppm      | ASTM D5185m  | >20        | 0           | 0           |          |
| Copper           | ppm      | ASTM D5185m  | >20        | 0           | 1           |          |
| Tin              | ppm      | ASTM D5185m  | >20        | 0           | 0           |          |
| Vanadium         | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Cadmium          | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| ADDITIVES        |          | method       | limit/base | current     | history1    | history2 |
| Boron            | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Barium           | ppm      | ASTM D5185m  |            | 0           | <1          |          |
| Molybdenum       | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Manganese        | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Magnesium        | ppm      | ASTM D5185m  |            | 9           | 49          |          |
| Calcium          | ppm      | ASTM D5185m  | 48         | 29          | 12          |          |
| Phosphorus       | ppm      | ASTM D5185m  | 337        | 300         | 323         |          |
| Zinc             | ppm      | ASTM D5185m  | 426        | 365         | 308         |          |
| Sulfur           | ppm      | ASTM D5185m  | 2280       | 802         | 973         |          |
| CONTAMINANTS     | 3        | method       | limit/base | current     | history1    | history2 |
| Silicon          | ppm      | ASTM D5185m  | >15        | 0           | 2           |          |
| Sodium           | ppm      | ASTM D5185m  |            | 0           | 1           |          |
| Potassium        | ppm      | ASTM D5185m  | >20        | 0           | <1          |          |
| FLUID CLEANLIN   | IESS     | method       | limit/base | current     | history1    | history2 |
| Particles >4µm   |          | ASTM D7647   | >2500      | 586         | 1589        |          |
| Particles >6μm   |          | ASTM D7647   | >320       | 144         | 252         |          |
| Particles >14µm  |          | ASTM D7647   | >80        | 18          | 24          |          |
| Particles >21µm  |          | ASTM D7647   | >20        | 4           | 7           |          |
| Particles >38µm  |          | ASTM D7647   | >4         | 0           | 1           |          |
| Particles >71µm  |          | ASTM D7647   | >3         | 0           | 0           |          |
| Oil Cleanliness  |          | ISO 4406 (c) | >18/15/13  | 16/14/11    | 18/15/12    |          |
| FLUID DEGRAD     | NOITA    | method       | limit/base | current     | history1    | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045   | .6         | 0.38        | 0.39        |          |



# **OIL ANALYSIS REPORT**







Certificate L2367

Laboratory Sample No. Lab Number Unique Number

: WC0752766 . 05848624 : 10472731 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 16 May 2023 : 18 May 2023 : Wes Davis Diagnostician

**TADANO MANTIS CORPORATION** 

2680 S FRONT ST RICHLANDS, VA US 24641

Contact: CHRIS RASNAKE chris.rasnake@tadano.com

T: F: (615)370-5670

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)