

OIL ANALYSIS REPORT

Sample Rating Trend



GTC 1200-85T

Component Hydraulic System Fluid SHELL TELLUS T32 (410 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM		method	limit/base	current	history1	history2
			mmubase			
Sample Number		Client Info		WC0776063	WC0736491	
Sample Date	1	Client Info		15 May 2023	29 Mar 2023	
Machine Age	hrs	Client Info		85	82	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Filtered	Filtered	
Sample Status				NORMAL	ABNORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	<1	
Chromium	ppm	ASTM D5185m	>20	0	0	
Nickel	ppm	ASTM D5185m	>20	0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	<1	
Aluminum	ppm	ASTM D5185m	>20	0	<1	
Lead	ppm	ASTM D5185m	>20	0	0	
Copper	ppm	ASTM D5185m	>20	0	1	
Tin	ppm	ASTM D5185m	>20	0	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		0	0	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m		10	52	
Calcium	ppm	ASTM D5185m	48	31	12	
Phosphorus	ppm	ASTM D5185m	337	321	320	
Zinc	ppm	ASTM D5185m	426	387	312	
Sulfur	ppm	ASTM D5185m	2280	838	990	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon		ASTM D5185m	>15	0	<u>↓</u> 50	
Sodium	ppm	ASTM D5185m	>15	0	1	
Potassium	ppm ppm	ASTM D5185m	>20	0	<1	
FLUID CLEANLIN		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>2500	763	▲ 3000	
Particles >6µm		ASTM D7647	>320	181	▲ 713	
Particles >14µm		ASTM D7647	>80	21	45	
Particles >21µm		ASTM D7647	>20	6	8	
Particles >38µm		ASTM D7647	>4	0	1	
Particles >71µm		ASTM D7647	>3	0	0	
Oil Cleanliness		ISO 4406 (c)	>18/15/13	0 17/15/12	▲ 19/17/13	
		()				
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	.6	0.40	0.39	




OIL ANALYSIS REPORT

VICLIAI







VISUAL		method	limit/base	e current	history1	history2
White Metal	scalar *	Visual	NONE	NONE	NONE	
Yellow Metal	scalar *	Visual	NONE	NONE	NONE	
Precipitate		Visual	NONE	NONE	NONE	
Silt		Visual	NONE	NONE	NONE	
Debris		Visual	NONE	NONE	NONE	
Sand/Dirt		Visual	NONE	NONE	NONE	
Appearance		Visual	NORML	NORML	NORML	
Odor Emulsified Water		Visual Visual	NORML >0.05	NORML NEG	NORML	
Free Water		Visual	>0.05	NEG	NEG	
FLUID PROPERT		method	limit/base		history1	history2
Visc @ 40°C		STM D445	32.21	33.4	32.1	
SAMPLE IMAGES		method	limit/base		history1	history2
SAWFLE IMAGE	5	method	iiiiii/base		TIISTOLY I	Thistory 2
Color						no image
Bottom						no image
GRAPHS						
Ferrous Alloys			491,5	Particle Coun	t	20
8- iron			431,3	520		7 ²⁶
E 6 - nickel			122,8	880 -		-24
8 4			30,7	720 Severe		-22
2			7.1	680		-20
0/23				Abnormal		20
Mar29,23			May15/23 s (per 1 m	920	•	-20 -18 -16 -14 -14 -12
Non-ferrous Metal	s		<u>a</u>	480		-16
10 copper			er of p	120-		-14
0 - management lead						
4				30-		-12
2-				8 -		-10
33			(23	2-		-8
Mar29/23			May15/23			
Viscosity @ 40°C			2	⁰ ⁴ μ 6μ Acid Number	14μ 21μ	38µ 71µ
38 36 Abnormal			(B)			
			0 KOH	0.60 - Base		
34 32 - Base			Acid Number (mg KOH/g)	.40		
Abnormal			N U	1.20 -		
26			May15/23	Mar29/23		Mav15/23
26			20	art		
: WearCheck USA - 5 : WC0776063 : 05848625	Received Diagnosed Diagnostic	:16 :18 ian :We	ary, NC 275 May 2023 May 2023 s Davis		RI Contact: CH	

To discuss this sample rep * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: CHRIS RASNAKE - SPAFRA

F: (615)370-5670