




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
P1
Machine Id
3104 - 3101 EVAPORATOR
Component
Gearbox
Fluid
MOBIL MOBILGEAR 600 XP ISO 150 (15 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	WC0810803	WC0752482	WC0724719
Sample Date	Client Info	31 May 2023	03 Feb 2023	20 Oct 2022
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	ATTENTION

WEAR METALS

method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m >200	110	98	67
Chromium	ppm	ASTM D5185m >15	1	1	<1
Nickel	ppm	ASTM D5185m >15	<1	<1	0
Titanium	ppm	ASTM D5185m	3	3	2
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >25	0	2	<1
Lead	ppm	ASTM D5185m >100	0	1	<1
Copper	ppm	ASTM D5185m >200	5	7	7
Tin	ppm	ASTM D5185m >25	<1	<1	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	<1	0

ADDITIVES

method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	41	45	39
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	3	3	3
Manganese	ppm	ASTM D5185m	2	2	1
Magnesium	ppm	ASTM D5185m	4	5	4
Calcium	ppm	ASTM D5185m	21	20	17
Phosphorus	ppm	ASTM D5185m	356	346	329
Zinc	ppm	ASTM D5185m	14	21	14
Sulfur	ppm	ASTM D5185m	18231	17168	16828

CONTAMINANTS

method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m >50	2	2	1
Sodium	ppm	ASTM D5185m	2	2	0
Potassium	ppm	ASTM D5185m >20	8	7	9
Water	%	ASTM D6304 >0.2	0.061	0.114	0.110
ppm Water	ppm	ASTM D6304 >2000	615.2	1146.5	1105.7

FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	106988	120017	113951
Particles >6µm	ASTM D7647 >40000	12433	18297	18735
Particles >14µm	ASTM D7647 >10000	106	182	273
Particles >21µm	ASTM D7647 >2500	13	20	36
Particles >38µm	ASTM D7647 >640	1	1	2
Particles >71µm	ASTM D7647 >160	0	0	0
Oil Cleanliness	ISO 4406 (c) >22/20	21/14	21/15	21/15

FLUID DEGRADATION

method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045	1.04	1.07	1.13



OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	HAZY	▲ HAZY
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	150	147	146

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0810803 **Received** : 05 Jun 2023
Lab Number : 05865123 **Diagnosed** : 06 Jun 2023
Unique Number : 10499588 **Diagnostician** : Wes Davis
Test Package : PLANT

AJINOMOTO USA
 4020 AJINOMOTO DRIVE
 RALEIGH, NC
 US 27610
 Contact: Michael Thompson
 thompsonm@ajiusa.com
 T: (919)723-2142
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)