

OIL ANALYSIS REPORT

Area Paper Machine Machine Id VALMET Winder Hydraulic

Component Hydraulic System Fluid MOBIL DTE 10 EXCEL 32 (317 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.







NORMAL


| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
|------------------|---------------|--------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | WC0776624 | | |
| Sample Date | | Client Info | | 13 Jun 2023 | | |
| Machine Age | hrs | Client Info | | 0 | | |
| Oil Age | hrs | Client Info | | 0 | | |
| Oil Changed | | Client Info | | N/A | | |
| Sample Status | | | | NORMAL | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >20 | 0 | | |
| Chromium | ppm | ASTM D5185m | >20 | 0 | | |
| Nickel | ppm | ASTM D5185m | >20 | 0 | | |
| Titanium | ppm | ASTM D5185m | | 0 | | |
| Silver | ppm | ASTM D5185m | | 0 | | |
| Aluminum | ppm | ASTM D5185m | >20 | 0 | | |
| Lead | ppm | ASTM D5185m | >20 | 0 | | |
| Copper | ppm | ASTM D5185m | >20 | <1 | | |
| Tin | ppm | ASTM D5185m | >20 | 0 | | |
| Vanadium | ppm | ASTM D5185m | | 0 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | | |
| Barium | ppm | ASTM D5185m | | 2 | | |
| Molybdenum | ppm | ASTM D5185m | | <1 | | |
| Manganese | ppm | ASTM D5185m | | 0 | | |
| Magnesium | ppm | ASTM D5185m | | <1 | | |
| Calcium | ppm | ASTM D5185m | 120 | 90 | | |
| Phosphorus | ppm | ASTM D5185m | 475 | 152 | | |
| Zinc | ppm | ASTM D5185m | | 55 | | |
| Sulfur | ppm | ASTM D5185m | 1275 | 1355 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | <1 | | |
| Sodium | ppm | ASTM D5185m | | 0 | | |
| Potassium | ppm | ASTM D5185m | >20 | <1 | | |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >5000 | 208 | | |
| Particles >6µm | | ASTM D7647 | >1300 | 79 | | |
| Particles >14µm | | ASTM D7647 | >160 | 13 | | |
| Particles >21µm | | ASTM D7647 | | 4 | | |
| Particles >38µm | | ASTM D7647 | >10 | 0 | | |
| Particles >71µm | | ASTM D7647 | | 0 | | |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | 15/13/11 | | |
| FLUID DEGRADA | | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | 0.14 | | |




OIL ANALYSIS REPORT









Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory

Sample No.

Lab Number

Submitted By: MARC-ANDRE HUBERT