




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
KANSAS/44
 Machine Id
78.262 [KANSAS^44]
 Component
Left Tandem
 Fluid
MOBIL MOBILTRANS HD 50 (17)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history 1	history 2
Sample Number	Client Info		WC0745982	WC0781252	WC0741692
Sample Date	Client Info		14 Jun 2023	23 May 2023	03 Oct 2022
Machine Age	hrs	Client Info	10155	10141	9859
Oil Age	hrs	Client Info	9873	156	9859
Oil Changed	Client Info		Changed	N/A	Changed
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history 1	history 2
Iron	ppm	ASTM D5185m >425	232	354	238
Chromium	ppm	ASTM D5185m >5	1	2	1
Nickel	ppm	ASTM D5185m >5	0	1	0
Titanium	ppm	ASTM D5185m	<1	<1	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >5	2	2	1
Lead	ppm	ASTM D5185m	0	0	0
Copper	ppm	ASTM D5185m >8	<1	0	0
Tin	ppm	ASTM D5185m	<1	0	0
Vanadium	ppm	ASTM D5185m	0	<1	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history 1	history 2
Boron	ppm	ASTM D5185m	32	39	34
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	<1	<1	<1
Manganese	ppm	ASTM D5185m	3	4	2
Magnesium	ppm	ASTM D5185m	18	17	14
Calcium	ppm	ASTM D5185m	3013	3424	3120
Phosphorus	ppm	ASTM D5185m	1009	1134	977
Zinc	ppm	ASTM D5185m	1249	1407	1194
Sulfur	ppm	ASTM D5185m	5772	6068	5839

CONTAMINANTS

	method	limit/base	current	history 1	history 2
Silicon	ppm	ASTM D5185m >50	9	10	9
Sodium	ppm	ASTM D5185m	18	21	17
Potassium	ppm	ASTM D5185m >20	0	2	0

VISUAL


	method	limit/base	current	history 1	history 2
White Metal	scalar	*Visual NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual NONE	NONE	NONE	NONE
Silt	scalar	*Visual NONE	NONE	NONE	NONE
Debris	scalar	*Visual NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual NONE	NONE	NONE	NONE
Appearance	scalar	*Visual NORML	NORML	NORML	NORML
Odor	scalar	*Visual NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual >0.2	NEG	NEG	NEG
Free Water	scalar	*Visual	NEG	NEG	NEG

FLUID PROPERTIES

	method	limit/base	current	history 1	history 2
Visc @ 40°C	cSt	ASTM D445 195	103	103	104






OIL ANALYSIS REPORT



SAMPLE IMAGES	method	limit/base	current	history 1	history 2
Color			no image	no image	no image
Bottom			no image	no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0745982 **Received** : 21 Jun 2023
Lab Number : 05879843 **Diagnosed** : 23 Jun 2023
Unique Number : 10524946 **Diagnostician** : Sean Felton
Test Package : CONST

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: RANDY ROBERTS
 randy.roberts@sherwood.net
 T: (316)943-6491
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)