

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id KAESER DSD 150 2704912 (S/N 1195) Component

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


	,					
SAMPLE INFORM	MATION	method	Jan 2016 Apr2017	Aug2018 May2020 Current	Jun2023 history1	history2
Sample Number		Client Info		KCPA002020	KCP39142	KCP26481
Sample Date		Client Info		22 Jun 2023	27 Sep 2021	27 May 2020
Machine Age	hrs	Client Info		84586	74106	67290
Dil Age	hrs	Client Info		0	8200	3300
Dil Changed		Client Info		N/A	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>50	0	<1	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	<1	0	<1
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	<1	<1
ead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	11	8	7
Tin	ppm	ASTM D5185m	>10	0	<1	0
Antimony	ppm	ASTM D5185m			0	0
/anadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	12	0
Barium	ppm	ASTM D5185m	90	0	0	12
Molybdenum	ppm	ASTM D5185m		0	0	<1
Manganese	ppm	ASTM D5185m		<1	0	0
<i>I</i> agnesium	ppm	ASTM D5185m	90	0	<1	14
Calcium	ppm	ASTM D5185m	2	4	0	<1
Phosphorus	ppm	ASTM D5185m		8	<1	<1
Zinc	ppm	ASTM D5185m		0	0	<1
Sulfur	ppm	ASTM D5185m		19163	12670	14014
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	0
Sodium	ppm	ASTM D5185m		<1	<1	<1
Potassium	ppm	ASTM D5185m	>20	2	0	1
Vater	%	ASTM D6304	>0.05	0.007	0.005	0.011
opm Water	ppm	ASTM D6304	>500	73.2	57.6	115.1
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		554	394	1259
Particles >6µm		ASTM D7647	>1300	203	63	196
Particles >14µm		ASTM D7647	>80	13	7	20
Particles >21µm		ASTM D7647	>20	5	2	11
Particles >38µm		ASTM D7647	>4	0	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Dil Cleanliness		ISO 4406 (c)	>/17/13	16/15/11	13/10	15/11
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.45	0.375	0.343
41:14) Rev: 1	Contact/Location: JESSY CARTER - BWAHOM					


Report Id: BWAHOM [WUSCAR] 05881534 (Generated: 07/18/2023 15:41:14) Rev: 1


Contact/Location: JESSY CARTER - BWAHOM



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	45.0	44.8	50.5
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				ij.		
Bottom				()		

ttom

