


# **OIL ANALYSIS REPORT**







# SUTPHEN 767

Component

**Hydraulic System** 

**DEXRON III (--- GAL)** 

#### Recommendation

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DEXRON III. Please confirm.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

				Jun2023		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0826466		
Sample Date		Client Info		27 Jun 2023		
Machine Age	hrs	Client Info		0		
Dil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>20	5		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	<1		
Γitanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>10	4		
_ead	ppm	ASTM D5185m	>10	2		
Copper	ppm	ASTM D5185m	>75	3		
rin	ppm	ASTM D5185m	>10	0		
/anadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		71		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		4		
Calcium	ppm	ASTM D5185m		150		
Phosphorus	ppm	ASTM D5185m		342		
Zinc	ppm	ASTM D5185m		125		
Sulfur	ppm	ASTM D5185m		1635		
CONTAMINANT	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	3		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	7		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPER	TIES	method	limit/base	current	history1	history2




## **OIL ANALYSIS REPORT**







#### **GRAPHS**



#### Non-ferrous Metals



## Viscosity @ 40°C





Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10560452 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0826466 Received : 14 Jul 2023 : 05899096 Diagnosed : 17 Jul 2023 Diagnostician : Wes Davis

1314 ROYAL PARKWAY EULESS, TX US 77073 Contact: B CLOUD BCLOUD@EULESSTX.GOV

**EULESS FIRE DEPT** 

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: