

OIL ANALYSIS REPORT

Sample Rating Trend

WEAR

HESSTON BALER W/SCALE

Diesel Engine

CHEVRON URSA SUPER PLUS EC 15W40 (--- QTS)

DIAGNOSIS

A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

🔺 Wear

The lead level is abnormal. All other component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORMA	TION	method	limit/base	current	history1	history2
Sample Number		Client Info		KL0007954		
Sample Date		Client Info		09 Jul 2023		
Machine Age	nrs	Client Info		2074		
Oil Age	nrs	Client Info		894		
Oil Changed		Client Info		Not Changd		
Sample Status				ABNORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
lron r	opm	ASTM D5185m	>100	40		
- 1	opm	ASTM D5185m		2		
	opm	ASTM D5185m	>4	0		
	opm	ASTM D5185m		<1		
	opm	ASTM D5185m	>3	0		
	opm	ASTM D5185m	>20	5		
	opm	ASTM D5185m	>40	A 75		
Copper p	opm	ASTM D5185m	>330	7		
	opm	ASTM D5185m	>15	<1		
Vanadium p	opm	ASTM D5185m		<1		
Cadmium p	opm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron p	opm	ASTM D5185m		188		
Barium p	opm	ASTM D5185m		0		
Molybdenum p	opm	ASTM D5185m		106		
Manganese p	opm	ASTM D5185m		<1		
Magnesium p	opm	ASTM D5185m		410		
Calcium p	opm	ASTM D5185m		2654		
Phosphorus p	opm	ASTM D5185m	1200	1102		
Zinc p	opm	ASTM D5185m	1300	1476		
Sulfur ß	opm	ASTM D5185m		5163		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon ß	opm	ASTM D5185m	>25	8		
	opm	ASTM D5185m		2		
Potassium p	opm	ASTM D5185m	>20	1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.2		
	Abs/cm	*ASTM D7624	>20	9.6		
Sulfation A	Abs/.1mm	*ASTM D7415	>30	23.9		




OIL ANALYSIS REPORT















回影 ١<u>.</u>

-189 B

FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2		
Particles >4µm		ASTM D7647		1583				
Particles >6µm		ASTM D7647	>5000	862				
Particles >14µm		ASTM D7647	>640	147				
Particles >21µm		ASTM D7647	>160	49				
Particles >38µm		ASTM D7647	>40	8				
Particles >71µm		ASTM D7647	>10	1				
Oil Cleanliness		ISO 4406 (c)	>19/16	17/14				
FLUID DEGRADA	TION	method	limit/base	current	history1	history2		
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.2				
Base Number (BN)	mg KOH/g	ASTM D2896	8.0	7.97				
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE				
Yellow Metal	scalar	*Visual	NONE	NONE				
Precipitate	scalar	*Visual	NONE	NONE				
Silt	scalar	*Visual	NONE	NONE				
Debris	scalar	*Visual	NONE	NONE				
Sand/Dirt	scalar	*Visual	NONE	NONE				
Appearance	scalar	*Visual	NORML	NORML				
Odor	scalar	*Visual	NORML	NORML				
Emulsified Water	scalar	*Visual	>0.2	NEG				
Free Water	scalar	*Visual		NEG				
FLUID PROPERT	IES	method	limit/base	current	history1	history2		
Visc @ 100°C	cSt	ASTM D445	15.4	16.6				
GRAPHS								
Ferrous Alloys								
T			491,520			T ²⁶		



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: LOUYER [WUSCAR] 05900159 (Generated: 07/19/2023 14:32:29) Rev: 1

Certificate L2367

Contact/Location: LOUIS SCATENA - LOUYER

F: (775)463-7412