




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
CONSTRUCTORS, INC
 Machine Id
CHEVROLET GASOLINE 03-0331
 Component
Gasoline Engine
 Fluid
MOBIL SUPER 5W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			SBP0004539	SBP0002296	SBP0000612
Sample Date	Client Info			14 Jul 2023	08 Dec 2022	20 Apr 2022
Machine Age	hrs	Client Info		9176	8900	8386
Oil Age	hrs	Client Info		276	282	332
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method		>4.0	<1.0	<1.0	<1.0
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	56	93	▲ 204
Chromium	ppm	ASTM D5185m	>20	2	4	7
Nickel	ppm	ASTM D5185m	>5	<1	1	3
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	1
Aluminum	ppm	ASTM D5185m	>40	9	17	▲ 31
Lead	ppm	ASTM D5185m	>50	0	<1	<1
Copper	ppm	ASTM D5185m	>155	10	10	15
Tin	ppm	ASTM D5185m	>10	<1	<1	1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		35	30	23
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		77	105	83
Manganese	ppm	ASTM D5185m		1	1	2
Magnesium	ppm	ASTM D5185m		508	530	527
Calcium	ppm	ASTM D5185m		1308	1395	1371
Phosphorus	ppm	ASTM D5185m		671	712	652
Zinc	ppm	ASTM D5185m		823	850	756
Sulfur	ppm	ASTM D5185m		3322	2958	2100



CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	15	15	▲ 32
Sodium	ppm	ASTM D5185m	>400	3	6	10
Potassium	ppm	ASTM D5185m	>20	5	6	0
Chlorine	ppm	ASTM D5185m		---	---	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	12.8	19.5	21.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.9	34.8	42.9

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.6	35.5	45.5
Base Number (BN)	mg KOH/g	ASTM D2896		4.8	4.3	▲ 2.8







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	10.4	10.2	10.2	10.9

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : SBP0004539 **Received** : 17 Jul 2023
Lab Number : **05900667** **Diagnosed** : 19 Jul 2023
Unique Number : 10562023 **Diagnostician** : Doug Bogart
Test Package : FLEET

Constructors Inc. - 603659
 1815 Y Street
 Lincoln, NE
 US 68508
 Contact: Jack Linhart
 jackl@constructorslincoln.com
 T: (402)434-2157
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)