


# **OIL ANALYSIS REPORT**

# <sup>Area</sup> [603777349 SR] 2 SLATE CONV PRI (S/N 20058864)

Component Gearbox

GEAR OIL ISO 460 (--- GAL)





### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0605493	WC0562054	WC0605156
Sample Number Sample Date		Client Info		16 Jun 2023	11 Dec 2022	23 Jun 2022
Machine Age	hrs	Client Info		0 Jun 2023	0 0	23 Jun 2022 0
Oil Age	hrs	Client Info		0	0	0
-	1115	Client Info		Not Changd	Changed	Not Changd
Oil Changed		Client mio		NORMAL	NORMAL	NORMAL
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	34	33	2
Chromium	ppm	ASTM D5185m	>15	<1	<1	0
Nickel	ppm	ASTM D5185m	>15	0	2	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	0	0
Lead	ppm	ASTM D5185m	>100	0	0	<1
Copper	ppm	ASTM D5185m	>200	1	0	0
Tin	ppm	ASTM D5185m	>25	0	0	0
Antimony	ppm	ASTM D5185m	>5			
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	2	4	6
Barium	ppm	ASTM D5185m	15	2	0	0
Molybdenum	ppm	ASTM D5185m	15	0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m	50	<1	<1	<1
Calcium	ppm	ASTM D5185m	50	4	1	0
Phosphorus	ppm	ASTM D5185m	350	145	96	194
Zinc	ppm	ASTM D5185m	100	3	<1	0
Sulfur	ppm	ASTM D5185m	12500	2117	1578	2582
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	2	1	2
Sodium	ppm	ASTM D5185m		0	2	0
Potassium	ppm	ASTM D5185m	>20	2	1	1
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	0.60	0.42	0.66
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	LIGHT	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual	20.2	NEG		RE NEGRSCHI
1 100 VValGI	Juanan	Visual		IILG	TO THE LOCAL PROPERTY OF THE PARTY OF THE PA	I AFFOR COOLII





## **OIL ANALYSIS REPORT**







FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	460	457	470	479
SAMPLE IMAG	GES	method	limit/base	current	history1	history2
Color						
Bottom						













Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** 

: WC0605493 : 05901384 : 10562740

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 18 Jul 2023 : 20 Jul 2023

Diagnostician : Don Baldridge

Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) MARS CHOCOLATE

2019 NORTH OAK PARK CHICAGO, IL US 60707

Contact: TONY FIORE tony.fiore@effem.com T: (773)745-2279

Contact/Location: TONY FIORE - MARSCHI