


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



DZ-306
Component

Right Final Drive

CAT TDTO SAE 50 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition

The condition of the oil is acceptable for the time in service.

			1	May2023		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0705326		
Sample Date		Client Info		05 May 2023		
Machine Age	hrs	Client Info		2240		
Oil Age	hrs	Client Info		2240		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	66		
Chromium	ppm	ASTM D5185m	>10	1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		9		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		11		
Calcium	ppm	ASTM D5185m	2980	3242		
Phosphorus	ppm	ASTM D5185m	1100	1122		
Zinc	ppm	ASTM D5185m	1270	1427		
Sulfur	ppm	ASTM D5185m		17883		
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	13		
Sodium	ppm	ASTM D5185m		5		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	LIGHT		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2

Visc @ 40°C

cSt


ASTM D445 195

Report Id: ECPROA [WUSCAR] 05901605 (Generated: 07/20/2023 12:41:18) Rev: 1

Contact/Location: EDDIE SECO - ECPROA




OIL ANALYSIS REPORT





SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image

GRAPHS



Non-ferrous Metals









Report Id: ECPROA [WUSCAR] 05901605 (Generated: 07/20/2023 12:41:19) Rev: 1

Laboratory Sample No. Lab Number

Unique Number : 10562961

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0705326 : 05901605

Received Diagnosed

: 18 Jul 2023 : 20 Jul 2023 Diagnostician : Don Baldridge

Test Package : FLEET (Additional Tests: PrtCount) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

E.C. PACE CO. 1811 HOLLINS RD. ROANOKE, VA US 24012 Contact: EDDIE SECO

ESECO@ECPACE.COM T: (276)266-5849 F: (540)343-6909

Contact/Location: EDDIE SECO - ECPROA