

OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id MACK TD-401

Component Rear Differential Fluid

GEAR OIL SAE 75W90 (--- GAL)

	<u> </u>
DIAGNOSI	5

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2	
Sample Number		Client Info		WC0705226			
Sample Date		Client Info		22 Jun 2023			
Machine Age	mls	Client Info		136256			
Oil Age	mls	Client Info		136256			
Oil Changed		Client Info		Not Changd			
Sample Status				NORMAL			
WEAR METALS		method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>870	263			
Chromium	ppm	ASTM D5185m	>8	2			
Nickel	ppm	ASTM D5185m	>25	10			
Titanium	ppm	ASTM D5185m	>4	<1			
Silver	ppm	ASTM D5185m		0			
Aluminum	ppm	ASTM D5185m	>40	2			
Lead	ppm	ASTM D5185m	>25	0			
Copper	ppm	ASTM D5185m	>60	2			
Tin	ppm	ASTM D5185m	>5	0			
Vanadium	ppm	ASTM D5185m		0			
Cadmium	ppm	ASTM D5185m		0			
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	400	180			
Barium	ppm	ASTM D5185m	200	<1			
Molybdenum		ASTM D5185m	12	<1			
	ppm	ASTM D5185m	12	6			
Manganese Magnesium	ppm	ASTM D5185m	12	ہ <1			
Calcium	ppm	ASTM D5185m	150	19			
	ppm	ASTM D5185m		-			
Phosphorus Zinc	ppm	ASTM D5185m	1650	1509 14			
Sulfur	ppm ppm	ASTM D5185m	125 22500	29998			
CONTAMINANTS		method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>285	135			
Sodium	ppm	ASTM D5185m		5			
Potassium	ppm	ASTM D5185m	>20	6			
VISUAL		method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	LIGHT			
Yellow Metal	scalar	*Visual	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE			
Debris	scalar	*Visual	NONE	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML			
Emulsified Water	scalar	*Visual	>.2	NEG			
Free Water	scalar	*Visual		NEG			
FLUID PROPERT	IES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D445	109	87.3			
2:42:07) Bev: 1	501		.00		Contact/Location: EDDIE SECO - ECPBOA		

Report Id: ECPROA [WUSCAR] 05901613 (Generated: 07/20/2023 12:42:07) Rev: 1

Contact/Location: EDDIE SECO - ECPROA



OIL ANALYSIS REPORT



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: EDDIE SECO - ECPROA