




## KAESER 8435979

Compressor Fluid KAESER SIGMA (OEM) S-460 (--- GAL)

### COMPONENT CONDITION SUMMARY



### RECOMMENDATION

Oil and filter change at the time of sampling has been noted. We were unable to perform a particle count due to a high concentration of particles present in this sample. We recommend an early resample in 500 hours to monitor this condition.

#### **PROBLEMATIC TEST RESULTS** Sample Status ABNORMAL NORMAL ASTM D6304 >0.05 Water % 0.221 0.029 ppm Water ASTM D6304 >500 2210 294.6 ppm Debris NONE scalar \*Visual MODER NONE Appearance scalar \*Visual NORML HAZY NORML **Emulsified Water** scalar \*Visual >0.05 ▲ 0.2% NEG


Customer Id: FANRIV Sample No.: KC101061 Lab Number: 05901905 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Don Baldridge +1 don.b505@comcast.net

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com



RECOMMENDED A	CTIONS			
Action	Status	Date	Done By	Description
Change Fluid			?	Oil and filter change at the time of sampling has been noted.
Change Filter			?	Oil and filter change at the time of sampling has been noted.
Alert			?	We were unable to perform a particle count due to a high concentration of particles present in this sample.

### HISTORICAL DIAGNOSIS



26 May 2023 Diag: Don Baldridge

Resample at the next service interval to monitor.All component wear rates are normal. The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





### **OIL ANALYSIS REPORT**

### Sample Rating Trend

WATER

# KAESER 8435979

Compressor Fluid KAESER SIGMA (OEM) S-460 (--- GAL)

### DIAGNOSIS

### Recommendation

Oil and filter change at the time of sampling has been noted. We were unable to perform a particle count due to a high concentration of particles present in this sample. We recommend an early resample in 500 hours to monitor this condition.

### Wear

All component wear rates are normal.

### Contamination

Moderate concentration of visible dirt/debris present in the oil. There is a light concentration of water present in the oil.


### Fluid Condition


The AN level is acceptable for this fluid.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KC101061	KC102785	
Sample Date		Client Info		05 Jul 2023	26 May 2023	
Machine Age	hrs	Client Info		1756	1456	
Oil Age	hrs	Client Info		1756	1456	
Oil Changed		Client Info		Changed	Not Changd	
Sample Status				ABNORMAL	NORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	1	2	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m	>3	0	0	
Titanium	ppm	ASTM D5185m	>3	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	<1	0	
Lead	ppm	ASTM D5185m	>10	<1	<1	
Copper	ppm	ASTM D5185m	>50	6	3	
Tin	ppm	ASTM D5185m	>10	<1	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES	1-1-		limit/base	-	la la tanan d	biotom (O
ADDITIVE5		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m	90	0	7	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m	90	44	67	
Calcium	ppm	ASTM D5185m	2	2	2	
Phosphorus	ppm	ASTM D5185m		2	3	
Zinc	ppm	ASTM D5185m		0	3	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	
Sodium	ppm	ASTM D5185m		7	14	
Potassium	ppm	ASTM D5185m	>20	9	9	
Water	%	ASTM D6304	>0.05	<u> </u>	0.029	
ppm Water	ppm	ASTM D6304	>500	<u> </u>	294.6	
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647			2176	
Particles >6µm		ASTM D7647	>1300		900	
Particles >14µm		ASTM D7647	>80		57	
Particles >21µm		ASTM D7647	>20		12	
Particles >38µm		ASTM D7647	>4		1	
Particles >71µm		ASTM D7647	>3		0	
Oil Cleanliness		ISO 4406 (c)	>/17/13		18/17/13	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.27	0.31	




## **OIL ANALYSIS REPORT**









To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory

Sample No.