




# PROBLEM SUMMARY

Sample Rating Trend

DIRT




Area  
**ROBIN B INGRAM**  
 Machine Id  
**[ROBIN B INGRAM] 003 617985-3**  
 Component  
**Starboard Main Engine**  
 Fluid  
**CHEVRON DELO 710 LE (250 GAL)**




## COMPONENT CONDITION SUMMARY


### ▲ Glycol Contamination




### ▲ Non-ferrous Metals



### ▲ Silicon (ppm)



### ▲ Aluminum (ppm)



## RECOMMENDATION

We advise that you check for the source of the coolant leak. Check for low coolant level. We advise that you check the air filter, air induction system, and any areas where dirt may enter the component. We recommend an early resample to monitor this condition.

## PROBLEMATIC TEST RESULTS

Sample Status				ABNORMAL	ATTENTION	NORMAL
Aluminum	ppm	ASTM D5185m	>15	▲ 6	<1	<1
Lead	ppm	ASTM D5185m	>18	▲ 38	21	10
Copper	ppm	ASTM D5185m	>80	▲ 38	13	16
Silicon	ppm	ASTM D5185m	>20	▲ 27	11	8
Sodium	ppm	ASTM D5185m	>75	▲ 214	▲ 76	37
Potassium	ppm	ASTM D5185m	>20	▲ 16	5	5

Customer Id: INGPAD  
 Sample No.: MW05901973  
 Lab Number: 05901973  
 Test Package: MAR 2



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Jonathan Hester +1 919-379-4092 x4092  
[jhester@wearcheckusa.com](mailto:jhester@wearcheckusa.com)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Resample	MISSED	Jul 20 2023	?	We recommend an early resample to monitor this condition.
Check Dirt Access	MISSED	Jul 20 2023	?	We advise that you check the air filter, air induction system, and any areas where dirt may enter the component.
Check Glycol Access	MISSED	Jul 20 2023	?	We advise that you check for the source of the coolant leak.

## HISTORICAL DIAGNOSIS

### 01 Jun 2023 Diag: Don Baldrige

#### COOLANT



No corrective action is recommended at this time. Resample at the next service interval to monitor. All component wear rates are normal. The high sodium (Na) level indicates the possible presence of salt water. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

[view report](#)



### 31 Mar 2023 Diag: Wes Davis

#### NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

[view report](#)



### 01 Mar 2023 Diag: Wes Davis

#### NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


[view report](#)





# OIL ANALYSIS REPORT

Sample Rating Trend



**DIRT**



Area  
**ROBIN B INGRAM**  
 Machine Id  
**[ROBIN B INGRAM] 003 617985-3**  
 Component  
**Starboard Main Engine**  
 Fluid  
**CHEVRON DELO 710 LE (250 GAL)**

## DIAGNOSIS

### Recommendation

We advise that you check for the source of the coolant leak. Check for low coolant level. We advise that you check the air filter, air induction system, and any areas where dirt may enter the component. We recommend an early resample to monitor this condition.

### Wear

Bearing and/or bushing wear is indicated.

### Contamination

Sodium and/or potassium levels are high. Elemental levels of silicon (Si) and aluminum (Al) indicate alumina-silicate (coarse dirt) ingress.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>MW05901973</b>	MW0027295	MW05875095
Sample Date	Client Info		<b>01 Jun 2023</b>	01 Jun 2023	31 Mar 2023
Machine Age	hrs	Client Info	<b>52520</b>	57848	57244
Oil Age	hrs	Client Info	<b>0</b>	57848	275
Oil Changed	Client Info		<b>N/A</b>	Not Changd	N/A
Sample Status			<b>ABNORMAL</b>	ATTENTION	NORMAL

## CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<b>&lt;1.0</b>	<1.0	<1.0

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >75	<b>25</b>	17	18
Chromium	ppm	ASTM D5185m >8	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m >2	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185m >3	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >15	<b>▲ 6</b>	<1	<1
Lead	ppm	ASTM D5185m >18	<b>▲ 38</b>	21	10
Copper	ppm	ASTM D5185m >80	<b>▲ 38</b>	13	16
Tin	ppm	ASTM D5185m >14	<b>2</b>	2	3
Vanadium	ppm	ASTM D5185m	<b>0</b>	<1	<1
Cadmium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	<b>58</b>	54	44
Barium	ppm	ASTM D5185m	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	<b>46</b>	44	48
Manganese	ppm	ASTM D5185m	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	<b>121</b>	51	42
Calcium	ppm	ASTM D5185m	<b>3264</b>	3394	3581
Phosphorus	ppm	ASTM D5185m	<b>8</b>	15	19
Zinc	ppm	ASTM D5185m 10	<b>24</b>	6	7
Sulfur	ppm	ASTM D5185m	<b>2427</b>	2669	2849

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	<b>▲ 27</b>	11	8
Sodium	ppm	ASTM D5185m >75	<b>▲ 214</b>	▲ 76	37
Potassium	ppm	ASTM D5185m >20	<b>▲ 16</b>	5	5
Glycol	%	*ASTM D2982	<b>NEG</b>	NEG	NEG

## INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	<b>0.4</b>	0.3	0.7
Nitration	Abs/cm	*ASTM D7624 >20	<b>7.1</b>	6.8	8.9
Sulfation	Abs/.1mm	*ASTM D7415 >30	<b>15.8</b>	15.6	17.4


## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	<b>6.4</b>	6.6	8.4
Base Number (BN)	mg KOH/g	ASTM D2896 9.2	<b>10.15</b>	10.60	9.55




# OIL ANALYSIS REPORT


### ▲ Silicon (ppm)




### ▲ Aluminum (ppm)




### ▲ Glycol Contamination



### Base Number



### Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.5	<b>14.1</b>	14.5	14.2

### GRAPHS


#### Ferrous Alloys




#### ▲ Non-ferrous Metals



#### Viscosity @ 100°C



#### Base Number



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : MW05901973 **Received** : 18 Jul 2023  
**Lab Number** : **05901973** **Diagnosed** : 20 Jul 2023  
**Unique Number** : 10563329 **Diagnostician** : Jonathan Hester  
**Test Package** : MAR 2 ( Additional Tests: Glycol )

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**INGRAM BARGE**  
 900 S 3RD ST  
 PADUCAH, KY  
 US 42003

Contact: DALE MORIE  
 dale.morie@ingrambarga.com  
 T: (270)415-4467  
 F: (615)695-3697