

No relevant graphs to display

RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

PROBLEMATIC TEST RESULTS							
Sample Status				ABNORMAL	ATTENTION	NORMAL	
Debris	scalar	*Visual	NONE	A MODER	NONE	NONE	

Customer Id: CARWYA Sample No.: USPM28457 Lab Number: 05902304 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Doug Bogart +1 (800)237-1369 x4016 <u>dougb@wearcheckusa.com</u>

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS						
Action	Status	Date	Done By	Description		
Change Filter			?	We recommend you service the filters on this component.		
Alert			?	We were unable to perform a particle count due to a high concentration of particles present in this sample.		

HISTORICAL DIAGNOSIS



20 Feb 2023 Diag: Doug Bogart

Resample at the next service interval to monitor.All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. A decrease in the phosphorus level is noted. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



view report

04 Jan 2021 Diag: Doug Bogart



 \checkmark

Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

22 Sep 2020 Diag: Jonathan Hester





Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.







OIL ANALYSIS REPORT

Sample Rating Trend **VIS DEBRIS**



GAL)			eb2017 Sep2	017 Apr2018 Oct2018	May2019 Nov2019 Jun2020 Jan	2021 Jul202:	
	SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
	Sample Number		Client Info		USPM28457	USPM26728	USPM5148980
ers on this	Sample Date		Client Info		18 Jul 2023	20 Feb 2023	04 Jan 2021
service interval to n a particle count cles present in	Machine Age	hrs	Client Info		0	0	0
	Oil Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Sample Status				ABNORMAL	ATTENTION	NORMAL
nal.	WEAR METALS		method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>90	0	0	2
lirt/debris present	Chromium	ppm	ASTM D5185m	>5	0	0	0
	Nickel	ppm	ASTM D5185m	>5	0	0	0
	Titanium	ppm	ASTM D5185m	>3	0	0	0
fluid. The	Silver	ppm	ASTM D5185m	>3	0	0	0
rther service.	Aluminum	ppm	ASTM D5185m	>7	<1	0	0
	Lead	ppm	ASTM D5185m	>12	0	0	<1
	Copper	ppm	ASTM D5185m	>30	0	0	<1
	Tin	ppm	ASTM D5185m	>9	0	0	<1
	Antimony	ppm	ASTM D5185m				0
	Vanadium	ppm	ASTM D5185m		0	0	0
	Cadmium	ppm	ASTM D5185m		0	0	0
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185m		0	0	<1
	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		0	0	0
	Manganese	ppm	ASTM D5185m		0	0	0
	Magnesium	ppm	ASTM D5185m		0	<1	0
	Calcium	ppm	ASTM D5185m		0	0	0
	Phosphorus	ppm	ASTM D5185m		195	1 43	1114
	Zinc	ppm	ASTM D5185m		0	0	0
	Sulfur	ppm	ASTM D5185m		0	0	55
	CONTAMINANTS	6	method	limit/base	current	history1	history2
	Silicon	ppm	ASTM D5185m	>60	6	4	2
	Sodium	ppm	ASTM D5185m		0	0	0
	Potassium	ppm	ASTM D5185m	>20	0	<1	0
	Water	%	ASTM D6304		0.003	0.007	0.038
	ppm Water	ppm	ASTM D6304	>.1	34.0	78.3	387.4
	FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
	Particles >4µm		ASTM D7647	>5000		4 9306	869
	Particles >6µm		ASTM D7647	>1300		<u> </u>	216
	Particles >14µm		ASTM D7647	>160		80	17
	Particles >21µm		ASTM D7647	>40		11	7
	Particles >38µm		ASTM D7647	>10		1	2
	Particles >71µm		ASTM D7647	>3		0	0
	Oil Cleanliness		ISO 4406 (c)	>19/17/14		▲ 20/18/13	17/15/11
	FLUID DEGRADA	TION	method	limit/base	current	history1	history2
	Acid Number (AN)	ma KOH/a			0.269	0.013	0 220

Machine Id

BEACH 1 BEACH (S/N 15301) Component Pump

Fluid BUSCH R-590 PUMP OIL (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filte component. Resample at the next se monitor. We were unable to perform due to a high concentration of partic this sample.

Wear

All component wear rates are norma

Contamination

Moderate concentration of visible di in the oil.

Fluid Condition

The AN level is acceptable for this fl condition of the oil is suitable for fur

Acid Number (AN)

mg KOH/g ASTM D8045


0.269 0.013 0.220


Report Id: CARWYA [WUSCAR] 05902304 (Generated: 07/20/2023 09:32:54) Rev: 1


Contact/Location: SERVICE MANAGER ? - CARWYA



OIL ANALYSIS REPORT









VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	🔺 MODER	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual		NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	120.8	93.5	93.5	144
SAMPLE IMAGES		method	limit/base	current	history1	history2
				Statistics of the local division of the	mus	

Color



Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Page 4 of 4

Contact/Location: SERVICE MANAGER ? - CARWYA