




OIL ANALYSIS REPORT



Area
OKLAHOMA/102/EG - DOZER
 Machine Id
36.34L [OKLAHOMA^102^EG - DOZER]
 Component
Left Final Drive
 Fluid
MOBIL DELVAC 1350 (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: 9043 hrs)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

Confirm oil type. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

| | method | limit/base | current | history1 | history2 |
|---------------|-------------|-------------|--------------------|-------------|-------------|
| Sample Number | Client Info | | WC0746893 | WC0603264 | WC0649343 |
| Sample Date | Client Info | | 15 Jul 2023 | 17 Jan 2023 | 26 Aug 2022 |
| Machine Age | hrs | Client Info | 9043 | 8131 | 7832 |
| Oil Age | hrs | Client Info | 6969 | 6969 | 6969 |
| Oil Changed | Client Info | | N/A | N/A | N/A |
| Sample Status | | | NORMAL | NORMAL | NORMAL |

WEAR METALS

| | method | limit/base | current | history1 | history2 |
|----------|--------|------------------|-----------|----------|----------|
| Iron | ppm | ASTM D5185m >800 | 48 | 40 | 39 |
| Chromium | ppm | ASTM D5185m >10 | 2 | 2 | 1 |
| Nickel | ppm | ASTM D5185m >5 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m >15 | 0 | <1 | <1 |
| Silver | ppm | ASTM D5185m >2 | 0 | 0 | <1 |
| Aluminum | ppm | ASTM D5185m >75 | 2 | 2 | 3 |
| Lead | ppm | ASTM D5185m >10 | 0 | 0 | <1 |
| Copper | ppm | ASTM D5185m >75 | 0 | <1 | <1 |
| Tin | ppm | ASTM D5185m >8 | 0 | <1 | <1 |
| Vanadium | ppm | ASTM D5185m | 0 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | 0 | 0 | 0 |

ADDITIVES

| | method | limit/base | current | history1 | history2 |
|------------|--------|-------------|--------------|----------|----------|
| Boron | ppm | ASTM D5185m | 2 | 3 | 5 |
| Barium | ppm | ASTM D5185m | 0 | 2 | 0 |
| Molybdenum | ppm | ASTM D5185m | 2 | 2 | 2 |
| Manganese | ppm | ASTM D5185m | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 17 | 10 | 10 |
| Calcium | ppm | ASTM D5185m | 1639 | 993 | 1147 |
| Phosphorus | ppm | ASTM D5185m | 768 | 592 | 659 |
| Zinc | ppm | ASTM D5185m | 682 | 415 | 457 |
| Sulfur | ppm | ASTM D5185m | 6098 | 4512 | 4124 |

CONTAMINANTS

| | method | limit/base | current | history1 | history2 |
|-----------|--------|------------------|-----------|----------|----------|
| Silicon | ppm | ASTM D5185m >400 | 24 | 20 | 23 |
| Sodium | ppm | ASTM D5185m | 0 | 2 | 0 |
| Potassium | ppm | ASTM D5185m >20 | 2 | <1 | 3 |

VISUAL


| | method | limit/base | current | history1 | history2 |
|------------------|--------|---------------|--------------|----------|----------|
| White Metal | scalar | *Visual NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual NONE | LIGHT | NONE | NONE |
| Sand/Dirt | scalar | *Visual NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | NEG | NEG | NEG |

FLUID PROPERTIES

| | method | limit/base | current | history1 | history2 |
|-------------|--------|---------------|------------|----------|----------|
| Visc @ 40°C | cSt | ASTM D445 208 | 158 | 153 | 154 |






OIL ANALYSIS REPORT



| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---------------|--------|------------|----------|----------|----------|
| Color | | | no image | no image | |
| Bottom | | | no image | no image | |

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0746893 **Received** : 20 Jul 2023
Lab Number : **05904015** **Diagnosed** : 24 Jul 2023
Unique Number : 10565371 **Diagnostician** : Don Baldrige
Test Package : CONST

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: DOUG KING
 doug.king@sherwood.net
 T: (316)617-3161
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)