




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Machine Id  
**T-605 (S/N 509892-1)**  
 Component  
**Agitator Gearbox**  
 Fluid  
**MOBIL MOBILGEAR 630 (9 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>WC05905440</b>	WC0507891	WCI2341351
Sample Date	Client Info			<b>23 Jul 2023</b>	16 Feb 2021	30 Jan 2019
Machine Age	mths	Client Info		<b>0</b>	0	0
Oil Age	mths	Client Info		<b>0</b>	0	0
Oil Changed	Client Info			<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	<b>5</b>	4	3
Chromium	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	0	0
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
Aluminum	ppm	ASTM D5185m	>25	<b>0</b>	0	<1
Lead	ppm	ASTM D5185m	>100	<b>0</b>	0	0
Copper	ppm	ASTM D5185m	>50	<b>1</b>	2	2
Tin	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Antimony	ppm	ASTM D5185m	>5	<b>---</b>	<1	1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<b>0</b>	1	1
Barium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>0</b>	0	0
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Calcium	ppm	ASTM D5185m		<b>0</b>	2	2
Phosphorus	ppm	ASTM D5185m		<b>223</b>	234	213
Zinc	ppm	ASTM D5185m		<b>97</b>	71	62
Sulfur	ppm	ASTM D5185m		<b>16479</b>	13360	18337

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	<b>2</b>	1	2
Sodium	ppm	ASTM D5185m		<b>0</b>	<1	<1
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	<1	<1


FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	<b>4980</b>	2246	---
Particles >6µm		ASTM D7647	>5000	<b>475</b>	261	---
Particles >14µm		ASTM D7647	>640	<b>23</b>	20	---
Particles >21µm		ASTM D7647	>160	<b>5</b>	6	---
Particles >38µm		ASTM D7647	>40	<b>1</b>	0	---
Particles >71µm		ASTM D7647	>10	<b>1</b>	0	---
Oil Cleanliness		ISO 4406 (c)	>21/19/16	<b>19/16/12</b>	18/15/11	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		<b>0.47</b>	0.200	0.472




# OIL ANALYSIS REPORT


Particle Trend




Acid Number



Viscosity @ 40°C



Particle Trend




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	220	197	196

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color




Bottom




## GRAPHS


Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C



Particle Count



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
 Sample No. : WC05905440  
 Lab Number : 05905440  
 Unique Number : 10566796  
 Test Package : IND 2 ( Additional Tests: PrtCount )

Received : 24 Jul 2023  
 Diagnosed : 25 Jul 2023  
 Diagnostician : Angela Borella

AVERY DENNISON CHEMICAL DIVISION  
 171 DRAKETOWN RD  
 MILL HALL, PA  
 US 17751  
 Contact: DONALD EYER  
 DONALD.EYER@AVERYDENNISON.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
 F: (570)748-1813