


### **PROBLEM SUMMARY**



## LINE 8 SIDE (S/N X56A0100033)

Gearbox Fluid SHELL OMALA 320 (15 GAL)

COMPONENT CONDITION SUMMARY

No relevant graphs to display

#### RECOMMENDATION

Check seals and/or filters for points of contaminant entry. No corrective action is recommended at this time. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS								
Sample Status				ABNORMAL	NORMAL	NORMAL		
Debris	scalar	*Visual	NONE	A MODER	LIGHT	LIGHT		

Customer Id: TAPFRA Sample No.: RP0021308 Lab Number: 05922266 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Angela Borella +1 800-237-1369 angela.borella@wearcheckusa.com

*To change component or sample information:* Customer Service +1 1-800-237-1369 <u>customerservice@wearcheck.com</u>

RECOMMENDED AC	ECOMMENDED ACTIONS					
Action	Status	Date	Done By	Description		
Check Seals			?	Check seals and/or filters for points of contaminant entry.		

### **HISTORICAL DIAGNOSIS**





Resample at the next service interval to monitor.All component wear rates are normal. The water content is negligible. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

# view report

view report


### 15 Aug 2022 Diag: Don Baldridge

06 Feb 2023 Diag: Wes Davis



Resample at the next service interval to monitor.All component wear rates are normal. The water content is negligible. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

02 Feb 2022 Diag: Wes Davis










### **OIL ANALYSIS REPORT**

SAMPLE INFORMATION method



current

history1

history2

### LINE 8 SIDE (S/N X56A0100033)

Component Gearbox Fluic

### SHELL OMALA 320 (15 GAL)

### DIAGNOSIS

Machine Id

### Recommendation

Check seals and/or filters for points of contaminant entry. No corrective action is recommended at this time. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

Moderate concentration of visible dirt/debris present in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				00.1101.11		
Sample Number		Client Info		RP0021308	RP0029314	RP0021529
Sample Date		Client Info		03 Aug 2023	06 Feb 2023	15 Aug 2022
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				ABNORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	92	77	72
Chromium	ppm	ASTM D5185m	>15	1	1	<1
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>25	2	0	2
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>200	<1	<1	<1
Tin	ppm	ASTM D5185m	>25	<1	0	<1
Antimony	ppm	ASTM D5185m	>5			
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5.5	7	7	11
Barium	ppm	ASTM D5185m	0.4	0	0	0
Molybdenum	ppm	ASTM D5185m	0.5	0	<1	<1
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m	23	0	<1	<1
Calcium	ppm	ASTM D5185m	13	29	27	37
Phosphorus	ppm	ASTM D5185m	450	278	237	227
Zinc	ppm	ASTM D5185m	9.9	7	9	18
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	4	4	3
Sodium	ppm	ASTM D5185m		2	0	0
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water	%	ASTM D6304	>0.2	0.013	0.003	0.003
ppm Water	ppm	ASTM D6304	>2000	138.0	29.2	31.3
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.53	0.54	0.49
( )						

limit/base




340 (0-320 (0-0+) 3300 280


260

Mav6/


Aug31/17

### **OIL ANALYSIS REPORT**





Bottom



Submitted By: GREG HESTER