


Machine Id

# **PROBLEM SUMMARY**



40 Component Turbine Fluid R&O OIL ISO 68 (--- QTS)

COMPONENT CONDITION SUMMARY

No relevant graphs to display

RECOMMENDATION PROBLEMATIC TEST RESULTS

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. We were unable to perform a particle count due to metal particles present in this sample.

PROBLEMATIC T	EST RE	SULTS				
Sample Status				ABNORMAL	ABNORMAL	ATTENTION
White Metal	scalar	*Visual	NONE	🔺 MODER	LIGHT	NONE

Customer Id: COLALB Sample No.: WC0813260 Lab Number: 05923383 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Don Baldridge +1 don.b505@comcast.net

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS						
Action	Status	Date	Done By	Description		
Change Filter			?	We recommend you service the filters on this component if applicable.		
Alert			?	We were unable to perform a particle count due to metal particles present in this sample.		

### HISTORICAL DIAGNOSIS



### 14 Sep 2022 Diag: Jonathan Hester

We recommend you service the filters on this component. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



view report

### 16 Nov 2021 Diag: Doug Bogart



No corrective action is recommended at this time. Resample at the next service interval to monitor.All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

### 08 Sep 2020 Diag: Don Baldridge





Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.







## **OIL ANALYSIS REPORT**

### Sample Rating Trend

### **VISUAL METAL**



### DIAGNOSIS

### Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. We were unable to perform a particle count due to metal particles present in this sample.

### 🔺 Wear

Moderate concentration of visible metal present. All component wear rates are normal.

### Contamination

No other contaminants were detected in the oil.

### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


# 2005 Au2005 Fe2007 Ma2008 Ju2009 De2010 Ju2015 Au2019

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0813260	WC0700752	WC0577572
Sample Date		Client Info		13 Aug 2023	14 Sep 2022	16 Nov 2021
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	ABNORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>15	4	5	10
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	<1	1	0
Lead	ppm	ASTM D5185m		0	0	0
Copper	ppm	ASTM D5185m	>5	3	3	1
Tin	ppm	ASTM D5185m	>5	0	0	0
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	<1
Barium	ppm	ASTM D5185m	5	<1	0	0
Molybdenum	ppm	ASTM D5185m	5	0	0	<1
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m	5	6	<1	<1
Calcium	ppm	ASTM D5185m	5	0	0	17
Phosphorus	ppm	ASTM D5185m	100	3	0	10
Zinc	ppm	ASTM D5185m	25	28	10	11
Sulfur	ppm	ASTM D5185m	1500	17	36	141
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	1	<1	2
Sodium	ppm	ASTM D5185m		1	0	0
Potassium	ppm	ASTM D5185m	>20	<1	1	0
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647			23224	33931
Particles >6µm		ASTM D7647	>1300		<b>4</b> 011	<b>1</b> 841
Particles >14µm		ASTM D7647	>160		<b>1</b> 85	19
Particles >21µm		ASTM D7647	>40		33	4
Particles >38µm		ASTM D7647	>10		3	0
Particles >71µm		ASTM D7647	>3		0	0
Oil Cleanliness		ISO 4406 (c)	>/17/14		A 22/19/15	<b>2</b> 2/18/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	A MODER	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.03	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
FLUID PROPERT Visc @ 40°C	T <mark>IES</mark> cSt	method ASTM D445	limit/base 68	current 66.3	history1 66.2	history2 66.4
	cSt					
Visc @ 40°C	cSt	ASTM D445	68	66.3	66.2	66.4



Ê

Contact/Location: STEPHEN MOSS - COLALB