



PROBLEM SUMMARY

Sample Rating Trend




DEGRADATION



Machine Id
2M 2M
 Component
Gearbox
 Fluid
NOT GIVEN (--- GAL)

COMPONENT CONDITION SUMMARY

▲ Non-ferrous Metals



▲ Acid Number



RECOMMENDATION

Resample at the next service interval to monitor.
 Please submit a sample of the new (unused) oil to establish a baseline. Please specify the brand, type, and viscosity of the oil on your next sample.

PROBLEMATIC TEST RESULTS

Sample Status				ABNORMAL	---	---
Tin	ppm	ASTM D5185m	>25	▲ 77	---	---
Acid Number (AN)	mg KOH/g	ASTM D8045		▲ 5.10	---	---

Customer Id: CONMUSAL
 Sample No.: KFS0003808
 Lab Number: 05923426
 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:
 Angela Borella +1 800-237-1369
angela.borella@wearcheckusa.com

To change component or sample information:
 Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Resample	---	---	?	Please submit a sample of the new (unused) oil to establish a baseline.
Information Required	---	---	?	Please specify the brand, type, and viscosity of the oil on your next sample.


HISTORICAL DIAGNOSIS



OIL ANALYSIS REPORT

Sample Rating Trend

DEGRADATION



Machine Id
2M 2M
 Component
Gearbox
 Fluid
NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please submit a sample of the new (unused) oil to establish a baseline. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

The tin level is abnormal. All other component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is above the recommended limit.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	KFS0003808	---	---
Sample Date	Client Info	13 Aug 2023	---	---
Machine Age	hrs Client Info	0	---	---
Oil Age	hrs Client Info	0	---	---
Oil Changed	Client Info	N/A	---	---
Sample Status		ABNORMAL	---	---

WEAR METALS

method	limit/base	current	history1	history2
Iron ppm ASTM D5185m	>200	0	---	---
Chromium ppm ASTM D5185m	>15	3	---	---
Nickel ppm ASTM D5185m	>15	0	---	---
Titanium ppm ASTM D5185m		<1	---	---
Silver ppm ASTM D5185m		0	---	---
Aluminum ppm ASTM D5185m	>25	<1	---	---
Lead ppm ASTM D5185m	>100	0	---	---
Copper ppm ASTM D5185m	>200	<1	---	---
Tin ppm ASTM D5185m	>25	▲ 77	---	---
Vanadium ppm ASTM D5185m		<1	---	---
Cadmium ppm ASTM D5185m		0	---	---

ADDITIVES

method	limit/base	current	history1	history2
Boron ppm ASTM D5185m		0	---	---
Barium ppm ASTM D5185m		<1	---	---
Molybdenum ppm ASTM D5185m		0	---	---
Manganese ppm ASTM D5185m		<1	---	---
Magnesium ppm ASTM D5185m		7	---	---
Calcium ppm ASTM D5185m		<1	---	---
Phosphorus ppm ASTM D5185m		233	---	---
Zinc ppm ASTM D5185m		20	---	---
Sulfur ppm ASTM D5185m		1321	---	---

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon ppm ASTM D5185m	>50	<1	---	---
Sodium ppm ASTM D5185m		1	---	---
Potassium ppm ASTM D5185m	>20	2	---	---






FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm ASTM D7647	>20000	2626	---	---
Particles >6µm ASTM D7647	>5000	639	---	---
Particles >14µm ASTM D7647	>640	31	---	---
Particles >21µm ASTM D7647	>160	7	---	---
Particles >38µm ASTM D7647	>40	1	---	---
Particles >71µm ASTM D7647	>10	0	---	---
Oil Cleanliness ISO 4406 (c)	>21/19/16	19/16/12	---	---

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN) mg KOH/g ASTM D8045		▲ 5.10	---	---

OIL ANALYSIS REPORT




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	56.1	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------


Color



no image

no image






Bottom



no image

no image

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KFS0003808 **Received** : 14 Aug 2023
Lab Number : 05923426 **Diagnosed** : 15 Aug 2023
Unique Number : 10603373 **Diagnostician** : Angela Borella
Test Package : IND 2 (Additional Tests: KF, PrtCount)

CONSTELLIUM
 4805 SECOND STREET
 MUSCLE SHOALS, AL
 US 35661
 Contact: Randy Nichols
 randall.nichols@constellium.com
 T: (256)386-6956
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)