




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
35173
 Component
Diesel Engine
 Fluid
NOT GIVEN (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		KL0012013	KLM2339436	KLM2339352
Sample Date	Client Info		25 Jul 2023	07 Apr 2023	10 Feb 2023
Machine Age	mls	Client Info	26770	21961	17148
Oil Age	mls	Client Info	0	0	17148
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	ABNORMAL	ABNORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	0.4
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	12	44	33
Chromium	ppm	ASTM D5185m >20	<1	2	2
Nickel	ppm	ASTM D5185m >4	0	<1	<1
Titanium	ppm	ASTM D5185m	<1	<1	<1
Silver	ppm	ASTM D5185m >3	<1	<1	0
Aluminum	ppm	ASTM D5185m >20	4	12	10
Lead	ppm	ASTM D5185m >40	0	0	4
Copper	ppm	ASTM D5185m >330	71	▲ 330	▲ 325
Tin	ppm	ASTM D5185m >15	<1	4	3
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	79	15	22
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	63	17	16
Manganese	ppm	ASTM D5185m	<1	3	3
Magnesium	ppm	ASTM D5185m	855	876	833
Calcium	ppm	ASTM D5185m	1352	1327	1367
Phosphorus	ppm	ASTM D5185m	1052	823	761
Zinc	ppm	ASTM D5185m	1244	975	960
Sulfur	ppm	ASTM D5185m	4118	3153	2921

CONTAMINANTS





	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	4	8	7
Sodium	ppm	ASTM D5185m	3	5	3
Potassium	ppm	ASTM D5185m >20	6	27	23

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.2	0.6	0.5
Nitration	Abs/cm	*ASTM D7624 >20	7.6	12.2	10.8
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.0	24.1	22.7



OIL ANALYSIS REPORT








FLUID CLEANLINESS	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		1322	1775	1375
Particles >6µm	ASTM D7647	>5000	720	967	749
Particles >14µm	ASTM D7647	>640	123	165	127
Particles >21µm	ASTM D7647	>160	41	55	43
Particles >38µm	ASTM D7647	>40	6	9	7
Particles >71µm	ASTM D7647	>10	1	1	1
Oil Cleanliness	ISO 4406 (c)	>19/16	17/14	17/15	17/14

FLUID DEGRADATION	method	limit/base	current	history1	history2	
Oxidation	Abs./1mm	*ASTM D7414	>25	15.0	20.8	18.9
Base Number (BN)	mg KOH/g	ASTM D2896		10.76	8.62	8.77

VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.9	10.6	10.4

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KL0012013 **Received** : 14 Aug 2023
Lab Number : **05923605** **Diagnosed** : 18 Aug 2023
Unique Number : 10603552 **Diagnostician** : Jonathan Hester
Test Package : MOB 2 (Additional Tests: PrtCount)

CITY & COUNTY HONOLULU
 99-999 IWAENA RD
 AIEA, HI
 US 96701
 Contact: CLYDE OMIJA
 comija@honolulu.gov
 T: (575)623-9952
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)