




PROBLEM SUMMARY

Sample Rating Trend



ISO



Machine Id

E-1 E-1

Component

Lube System

Fluid

MOBIL DTE OIL EXTRA HEAVY (--- GAL)

COMPONENT CONDITION SUMMARY

▲ Particle Trend



RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS

Sample Status	ASTM D7647	ASTM D7647	ABNORMAL	NORMAL	---
Particles >4µm	ASTM D7647	>5000	▲ 100917	---	---
Particles >6µm	ASTM D7647	>1300	▲ 26765	---	---
Particles >14µm	ASTM D7647	>160	▲ 772	---	---
Particles >21µm	ASTM D7647	>40	▲ 130	---	---
Oil Cleanliness	ISO 4406 (c)	>19/17/14	▲ 24/22/17	---	---

Customer Id: TESAUSTLC

Sample No.: TLC0000998

Lab Number: 05924188

Test Package: PLANT



To manage this report scan the QR code

To discuss the diagnosis or test data:

Doug Bogart +1 (800)237-1369 x4016

dougb@wearcheckusa.com

To change component or sample information:

Customer Service +1 1-800-237-1369

customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Filter	---	---	?	We recommend you service the filters on this component.

HISTORICAL DIAGNOSIS

25 May 2023 Diag: Jonathan Hester

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


view report





OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id

E-1 E-1

Component

Lube System

Fluid

MOBIL DTE OIL EXTRA HEAVY (--- GAL)

DIAGNOSIS

▲ Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

▲ Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	TLC0000998	TLC0001161	---
Sample Date	Client Info	14 Aug 2023	25 May 2023	---
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	---
Sample Status		ABNORMAL	NORMAL	---

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >20	1	1
Chromium	ppm	ASTM D5185m >20	0	0
Nickel	ppm	ASTM D5185m >20	0	0
Titanium	ppm	ASTM D5185m	0	0
Silver	ppm	ASTM D5185m	0	0
Aluminum	ppm	ASTM D5185m >20	0	0
Lead	ppm	ASTM D5185m >20	0	2
Copper	ppm	ASTM D5185m >20	3	3
Tin	ppm	ASTM D5185m >20	0	0
Vanadium	ppm	ASTM D5185m	0	0
Cadmium	ppm	ASTM D5185m	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0
Barium	ppm	ASTM D5185m	0	2
Molybdenum	ppm	ASTM D5185m	0	0
Manganese	ppm	ASTM D5185m	0	0
Magnesium	ppm	ASTM D5185m	1	<1
Calcium	ppm	ASTM D5185m	103	1
Phosphorus	ppm	ASTM D5185m	399	24
Zinc	ppm	ASTM D5185m	506	2
Sulfur	ppm	ASTM D5185m	10771	3763

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	7	11
Sodium	ppm	ASTM D5185m	<1	0
Potassium	ppm	ASTM D5185m >20	0	<1

FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >5000	▲ 100917	---	---
Particles >6µm	ASTM D7647 >1300	▲ 26765	---	---
Particles >14µm	ASTM D7647 >160	▲ 772	---	---
Particles >21µm	ASTM D7647 >40	▲ 130	---	---
Particles >38µm	ASTM D7647 >10	4	---	---
Particles >71µm	ASTM D7647 >3	1	---	---
Oil Cleanliness	ISO 4406 (c) >19/17/14	▲ 24/22/17	---	---

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.81	0.077




OIL ANALYSIS REPORT


Particle Trend



Particle Trend



Acid Number



Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	146	149	144

SAMPLE IMAGES


method	limit/base	current	history1	history2
Color				
Bottom				

GRAPHS

Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C



Particle Count



Acid Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TLC0000998 **Received** : 14 Aug 2023
Lab Number : 05924188 **Diagnosed** : 15 Aug 2023
Unique Number : 10604135 **Diagnostician** : Doug Bogart
Test Package : PLANT

TESLA
 1 Tesla Road, BIW E58
 Austin, TX
 US 78725
 Contact: Dave Mitchell
 davmitchell@tesla.com
 T: (260)226-1968
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)