

No relevant graphs to display

	ON 41		ATIC	NN I
REC		/END	ALIC	JN

We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

PROBLEMATIC TEST RESULTS								
Sample Status				ABNORMAL	NORMAL	ABNORMAL		
Debris	scalar	*Visual	NONE	🔺 MODER	NONE	LIGHT		

Customer Id: CALSAL Sample No.: KCPA005094 Lab Number: 05924309 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Don Baldridge +1 <u>don.b505@comcast.net</u>

To change component or sample information: Customer Service +1 1-800-237-1369 <u>customerservice@wearcheck.com</u>

RECOMMENDED ACTIONS							
Action	Status	Date	Done By	Description			
Change Filter			?	We recommend you service the filters on this component.			
Alert			?	We were unable to perform a particle count due to a high concentration of particles present in this sample.			

HISTORICAL DIAGNOSIS



01 Jul 2022 Diag: Angela Borella

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



12 Aug 2021 Diag: Don Baldridge



No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





OIL ANALYSIS REP

Oil Age

Iron

Nickel

Silver

Titanium

Aluminum Lead Copper Tin Antimony Vanadium Cadmium

Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc

Chromium

Machine Id KAESER BSD 40T 6254735 (S/N 10 Component

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SIS REPC	RT	Samp	le Rating Tre	nd	VI	S DEBRIS
(S/N 1017	-	Automatical	ten limit/base	Judozz Augtor Current	, history1	history2
Sample Number		Client Info		KCPA005094	KCP40581	KCP41602
Sample Date		Client Info		03 Aug 2023	01 Jul 2022	12 Aug 2021
Machine Age	hrs	Client Info		29111	25312	21890
Oil Age	hrs	Client Info		0	2700	2000
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				ABNORMAL	NORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	<1	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum		ACTI DELCE	>10	<1	2	0
	ppm	ASTM D5185m	>10	<1 <1	2	0
Lead	ppm	ASTM D5185m ASTM D5185m	>10	0	<1	0
Lead Copper						
	ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>10	0 8 <1	<1 9 <1	0 15 0
Copper	ppm ppm	ASTM D5185m ASTM D5185m	>10 >50	0 8 <1 	<1 9	0 15
Copper Tin Antimony	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50	0 8 <1 0	<1 9 <1	0 15 0
Copper Tin Antimony Vanadium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50	0 8 <1 	<1 9 <1	0 15 0 0
Copper Tin	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50	0 8 <1 0	<1 9 <1 0	0 15 0 0 0
Copper Tin Antimony Vanadium Cadmium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50 >10	0 8 <1 0 0	<1 9 <1 0 0	0 15 0 0 0 0
Copper Tin Antimony Vanadium Cadmium ADDITIVES	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method	>10 >50 >10 limit/base	0 8 <1 0 0 0 current	<1 9 <1 0 0 0 history1	0 15 0 0 0 0 0 0 history2
Copper Tin Antimony Vanadium Cadmium ADDITIVES Boron	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m	>10 >50 >10 limit/base 0	0 8 <1 0 0 0 current 0	<1 9 <1 0 0 0 history1 0	0 15 0 0 0 0 0 history2 0
Copper Tin Antimony Vanadium Cadmium ADDITIVES Boron Barium	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50 >10 limit/base 0 90	0 8 <1 0 0 0 current 0 0	<1 9 <1 0 0 0 <u>history1</u> 0 3	0 15 0 0 0 0 0 history2 0 0
Copper Tin Antimony Vanadium Cadmium ADDITIVES Boron Barium Molybdenum	ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50 >10 limit/base 0 90	0 8 <1 0 0 0 <u>current</u> 0 0 0	<1 9 <1 0 0 0 history1 0 3 0	0 15 0 0 0 0 0 history2 0 0 0 0
Copper Tin Antimony Vanadium Cadmium ADDITIVES Boron Barium Molybdenum Manganese	ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50 >10 limit/base 0 90 0	0 8 <1 0 0 0 0 0 0 0 0 <1	<1 9 <1 0 0 0 history1 0 3 0 0 0	0 15 0 0 0 0 0 history2 0 0 0 0 0 0
Copper Tin Antimony Vanadium Cadmium ADDITIVES Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>10 >50 >10 limit/base 0 90 0 100	0 8 <1 0 0 0 0 0 0 0 <1 9	<1 9 <1 0 0 0 history1 0 3 0 0 0 11	0 15 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0

Sulfur	ppm	ASTM D5185m	23500	21999	23309	17739
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	<1
Sodium	ppm	ASTM D5185m		4	3	<1
Potassium	ppm	ASTM D5185m	>20	<1	1	0
Water	%	ASTM D6304	>0.05	0.016	0.011	0.006
ppm Water	ppm	ASTM D6304	>500	166.8	118.6	61.8

FLUID CLEANLINESS	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647			1405	15953
Particles >6µm	ASTM D7647	>1300		481	4 347
Particles >14µm	ASTM D7647	>80		41	A 390
Particles >21µm	ASTM D7647	>20		14	1 04
Particles >38µm	ASTM D7647	>4		1	4 9
Particles >71µm	ASTM D7647	>3		0	0
Oil Cleanliness	ISO 4406 (c)	>/17/13		18/16/13	▲ 19/16
FLUID DEGRADATION	method	limit/base	current	history1	history2

0.44

Acid Number (AN)

mg KOH/g ASTM D8045 1.0


0.45


Contact/Location: ? ? - CALSAL


0.441



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	🔺 MODER	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	FIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45	49.5	49.6	51.5
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color						



Bottom



Certificate L2367