




OIL ANALYSIS REPORT

Sample Rating Trend



WEAR



Machine Id
ALSTOM R157

Component
Gearbox

Fluid
TOTAL CARTER SH 220 (3 GAL)

DIAGNOSIS

▲ Recommendation

No corrective action is recommended at this time. We recommend an early resample to monitor this condition.

▲ Wear

Gear wear is indicated.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0781622	WC0667735	WC0560257
Sample Date	Client Info		31 Jul 2023	12 Nov 2022	15 Nov 2021
Machine Age	hrs	Client Info	0	0	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		Not Chngd	Not Chngd	N/A
Sample Status			ABNORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >200	▲ 207	97	135
Chromium	ppm	ASTM D5185m >10	1	<1	1
Nickel	ppm	ASTM D5185m >10	<1	<1	<1
Titanium	ppm	ASTM D5185m	0	0	<1
Silver	ppm	ASTM D5185m	0	0	<1
Aluminum	ppm	ASTM D5185m >25	5	3	4
Lead	ppm	ASTM D5185m >50	4	3	3
Copper	ppm	ASTM D5185m >200	63	49	53
Tin	ppm	ASTM D5185m >10	<1	<1	<1
Antimony	ppm	ASTM D5185m >5	---	---	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	1	<1	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	2
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1
Manganese	ppm	ASTM D5185m	2	1	1
Magnesium	ppm	ASTM D5185m	2	1	<1
Calcium	ppm	ASTM D5185m	8	9	6
Phosphorus	ppm	ASTM D5185m	395	323	298
Zinc	ppm	ASTM D5185m	142	107	71
Sulfur	ppm	ASTM D5185m	4280	4126	2598

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >50	26	16	24
Sodium	ppm	ASTM D5185m	26	23	25
Potassium	ppm	ASTM D5185m >20	4	1	<1

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.54	0.46	0.458


VISUAL

	method	limit/base	current	history1	history2
White Metal	scalar	*Visual NONE	LIGHT	LIGHT	LIGHT
Yellow Metal	scalar	*Visual NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual NONE	NONE	NONE	NONE
Silt	scalar	*Visual NONE	NONE	NONE	NONE
Debris	scalar	*Visual NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual NONE	NONE	NONE	NONE
Appearance	scalar	*Visual NORML	NORML	NORML	NORML
Odor	scalar	*Visual NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual >0.2	NEG	NEG	NEG
Free Water	scalar	*Visual	NEG	NEG	NEG




OIL ANALYSIS REPORT


▲ Ferrous Alloys



Acid Number



Viscosity @ 40°C



FLUID PROPERTIES


method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D445	244	237	234

SAMPLE IMAGES


method	limit/base	current	history1	history2
Color			no image	no image
Bottom			no image	no image

GRAPHS


▲ Iron (ppm)




Lead (ppm)




Aluminum (ppm)




Chromium (ppm)




Copper (ppm)




Silicon (ppm)



Viscosity @ 40°C



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0781622 **Received** : 14 Aug 2023
Lab Number : 05924438 **Diagnosed** : 16 Aug 2023
Unique Number : 10604385 **Diagnostician** : Jonathan Hester
Test Package : MOB 2

AMTRAK
 1401 W STREET NE, HIGH SPEED RAIL 2ND FLOOR
 WASHINGTON, DC
 US 20018
 Contact: MICHAEL PORTER
 michael.porter@amtrak.com
 T: (202)870-1399
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)