




# PROBLEM SUMMARY

Sample Rating Trend





**WEAR**



Area  
**FRONTIER II**  
 Machine Id  
**33WEA86925**  
 Component  
**Grease**  
 Fluid  
**NOT GIVEN (--- LTR)**

## COMPONENT CONDITION SUMMARY



## RECOMMENDATION

Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level.

## PROBLEMATIC TEST RESULTS

Sample Status			<b>ABNORMAL</b>	ABNORMAL	---	
PQ	ASTM D8184	>200	▲ <b>968</b>	▲ 689	---	
Iron	ppm	ASTM D5185m	>250	▲ <b>287</b>	▲ 364	---

Customer Id: NORDEX  
 Sample No.: NX05924616  
 Lab Number: 05924616  
 Test Package: GRS 1



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Doug Bogart +1 (800)237-1369 x4016  
[dougb@wearcheckusa.com](mailto:dougb@wearcheckusa.com)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Monitor	---	---	?	Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level.
Change Fluid	---	---	?	Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level.
Resample	---	---	?	Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level.

## HISTORICAL DIAGNOSIS

07 Jun 2023 Diag: Doug Bogart

### WEAR



Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level. Bearing and/or bushing wear is indicated. There is no indication of any contamination in the grease. The condition of the grease is acceptable for the time in service.


view report





# GREASE ANALYSIS

Sample Rating Trend



Area  
**FRONTIER II**  
 Machine Id  
**33WEA86925**  
 Component  
**Grease**  
 Fluid  
**NOT GIVEN (--- LTR)**

## DIAGNOSIS

### Recommendation

Re-sample to verify the actual oil condition. Purge old grease if still abnormal and monitor the trend of iron level.

### Wear

Bearing and/or bushing wear is indicated.

### Grease Condition

The condition of the grease is acceptable for the time in service.

### Contaminants

There is no indication of any contamination in the grease.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>NX05924616</b>	NX05884823	---
Sample Date	Client Info		<b>19 Jun 2023</b>	07 Jun 2023	---
Machine Age	hrs	Client Info	<b>0</b>	0	---
Grease Age	hrs	Client Info	<b>0</b>	0	---
Grease Serviced	Client Info		<b>N/A</b>	N/A	---
Sample Status			<b>ABNORMAL</b>	ABNORMAL	---

## WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184	>200	<b>▲ 968</b>	▲ 689	---
Iron	ppm	ASTM D5185m	>250	<b>▲ 287</b>	▲ 364
Chromium	ppm	ASTM D5185m	>10	<b>2</b>	3
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	0
Cadmium	ppm	ASTM D5185m		<b>&lt;1</b>	<1
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1
Vanadium	ppm	ASTM D5185m		<b>1</b>	1
Lead	ppm	ASTM D5185m	>25	<b>&lt;1</b>	<1
Copper	ppm	ASTM D5185m	>75	<b>39</b>	33
Tin	ppm	ASTM D5185m	>5	<b>0</b>	0
Silver	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<b>158</b>	160
Magnesium	ppm	ASTM D5185m		<b>0</b>	0
Manganese	ppm	ASTM D5185m		<b>3</b>	4
Molybdenum	ppm	ASTM D5185m		<b>3361</b>	4068
Phosphorus	ppm	ASTM D5185m		<b>807</b>	736
Zinc	ppm	ASTM D5185m		<b>125</b>	130

## THICKENER/SOAP


	method	limit/base	current	history1	history2
Aluminum	ppm	ASTM D5185m		<b>0</b>	0
Barium	ppm	ASTM D5185m		<b>10</b>	10
Calcium	ppm	ASTM D5185m		<b>19</b>	20
Sodium	ppm	ASTM D5185m		<b>12</b>	9
Lithium	ppm	ASTM D5185m		<b>3044</b>	3382
Sulfur	ppm	ASTM D5185m		<b>4607</b>	4802

## CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>150	<b>59</b>	70
Potassium	ppm	ASTM D5185m		<b>2</b>	<1






# GREASE ANALYSIS



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					no image
Bottom					no image
PrtFilter			no image	no image	no image



## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : NX05924616 **Received** : 14 Aug 2023  
**Lab Number** : 05924616 **Diagnosed** : 22 Aug 2023  
**Unique Number** : 10604563 **Diagnostician** : Doug Bogart  
**Test Package** : GRS 1 ( Additional Tests: KV40, SCREEN )

**NORDEX USA - Chicago**  
 300 SOUTH WACKER DRIVE, SUITE 1500  
 CHICAGO, IL  
 US 60606  
 Contact: DEVIN LINEHAN  
 DLinehan@nordex-online.com  
 T: (312)386-4124  
 F: (312)386-7102

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)