


PROBLEM SUMMARY

KAESER SFC 110S 2880079 (S/N 1014)

Compressor Fluid

KAESER SIGMA (OEM) S-460 (--- GAL)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

| PROBLEMATIC TE | ST RESULTS | | | | |
|-----------------|--------------|---------|-------------------|-------------|----------|
| Sample Status | | | ABNORMAL | ABNORMAL | ABNORMAL |
| Particles >6µm | ASTM D7647 | >1300 | A 3126 | ▲ 3694 | |
| Particles >14µm | ASTM D7647 | >80 | 🔺 189 | 2 09 | |
| Particles >21µm | ASTM D7647 | >20 | <u> </u> | A 33 | |
| Oil Cleanliness | ISO 4406 (c) | >/17/13 | A 21/19/15 | 🔺 21/19/15 | |


Customer Id: LATBET Sample No.: KCPA005028 Lab Number: 05925464 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Jonathan Hester +1 919-379-4092 x4092 jhester@wearcheckusa.com

To change component or sample information: Customer Service +1 1-800-237-1369 <u>customerservice@wearcheck.com</u>



| RECOMMENDED ACTIONS | | | | | |
|---------------------|--------|------|---------|---|--|
| Action | Status | Date | Done By | Description | |
| Change Filter | | | ? | We recommend you service the filters on this component. | |

HISTORICAL DIAGNOSIS



05 Dec 2022 Diag: Jonathan Hester

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

25 May 2022 Diag: Jonathan Hester

VIS DEBRIS



No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.All component wear rates are normal. Moderate concentration of visible dirt/debris present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



05 Nov 2021 Diag: Don Baldridge

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.All component wear rates are normal. Moderate concentration of visible dirt/debris present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





view report





OIL ANALYSIS REPORT

Machine Id KAESER SFC 110S 2880079 (S/N 1014) Component

Compressor Fluid

KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|----------|--------------|------------|--------------------|-------------------|-------------|
| Sample Number | | Client Info | | KCPA005028 | KCP53363 | KCP40735 |
| Sample Date | | Client Info | | 27 Jul 2023 | 05 Dec 2022 | 25 May 2022 |
| Machine Age | hrs | Client Info | | 65101 | 62503 | 59949 |
| Oil Age | hrs | Client Info | | 0 | 2554 | 4636 |
| Oil Changed | | Client Info | | N/A | Not Changd | Changed |
| Sample Status | | | | ABNORMAL | ABNORMAL | ABNORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >50 | <1 | <1 | 1 |
| Chromium | ppm | ASTM D5185m | >10 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | <1 |
| Aluminum | ppm | ASTM D5185m | >10 | <1 | 0 | <1 |
| Lead | ppm | | >10 | 0 | 0 | 0 |
| Copper | ppm | ASTM D5185m | | 2 | <1 | 1 |
| Tin | ppm | ASTM D5185m | >10 | 0 | <1 | 0 |
| Antimony | ppm | ASTM D5185m | - | | | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | 10 p | method | limit/base | current | history1 | history2 |
| | | | minubase | | | |
| Boron | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Barium | ppm | ASTM D5185m | 90 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | 0.0 | 0 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | 90 | 33 | 49 | 36 |
| Calcium | ppm | ASTM D5185m | 2 | 0 | 0 | 0 |
| Phosphorus | ppm | ASTM D5185m | | <1 | 10 | 6 |
| Zinc | ppm | ASTM D5185m | | 27 | 37 | 36 |
| Sulfur | ppm | ASTM D5185m | | 21815 | 21436 | 18306 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 1 | <1 | 1 |
| Sodium | ppm | ASTM D5185m | | 15 | 30 | 23 |
| Potassium | ppm | ASTM D5185m | | 5 | 5 | 3 |
| Water | % | ASTM D6304 | | 0.024 | 0.022 | 0.037 |
| opm Water | ppm | ASTM D6304 | >500 | 248.2 | 227.9 | 377.0 |
| FLUID CLEANLIN | ESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | | 10412 | 13400 | |
| Particles >6µm | | ASTM D7647 | >1300 | <u> </u> | A 3694 | |
| Particles >14µm | | ASTM D7647 | >80 | <mark>人</mark> 189 | <u> </u> | |
| Particles >21µm | | ASTM D7647 | >20 | <u> </u> | <mark>▲</mark> 33 | |
| Particles >38µm | | ASTM D7647 | >4 | 1 | 2 | |
| Particles >71µm | | ASTM D7647 | >3 | 0 | 0 | |
| Oil Cleanliness | | ISO 4406 (c) | >/17/13 | A 21/19/15 | 1 /19/15 | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.4 | 0.35 | 0.34 | 0.33 |
| 58-32) Boy: 1 | | | | stact/Location: S | | |


Report Id: LATBET [WUSCAR] 05925464 (Generated: 08/17/2023 13:58:32) Rev: 1


Contact/Location: SERVICE MANAGER - LATBET


Page 3 of 4



OIL ANALYSIS REPORT







Viscosity @ 40°C


52


5

48 34 (10-0) 44 (20-0)


43

40 - Abnom





Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Page 4 of 4

F: