


PROBLEM SUMMARY

Area North Plant-Crystallization Machine Id PU-2512J Component

Hydraulic System

HIGH PERFORMANCE LUBRICANTS HYDRAULIC LIFE 46 (20 GAL)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS Sample Status ABNORMAL **ATTENTION** ABNORMAL Particles >4µm ASTM D7647 >640 2368 **A** 861 **1**263 Particles >6µm ASTM D7647 >160 636 **2**98 **3**71 ASTM D7647 >40 Particles >14µm 64 24 🔺 44 Particles >21µm ASTM D7647 >10 **1**4 7 **1**1 **Oil Cleanliness** ISO 4406 (c) >16/14/12 🔺 18/16/13 🔺 17/15/12 🔺 17/16/13


Customer Id: AJIEDD Sample No.: WC0786776 Lab Number: 05926108 Test Package: PLANT



To manage this report scan the QR code

To discuss the diagnosis or test data: Doug Bogart +1 (800)237-1369 x4016 <u>dougb@wearcheckusa.com</u>

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com



RECOMMENDED ACTIONS						
Action	Status	Date	Done By	Description		
Change Filter			?	We recommend you service the filters on this component.		

HISTORICAL DIAGNOSIS



23 Jan 2023 Diag: Don Baldridge

No corrective action is recommended at this time. Resample at the next service interval to monitor.All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



view report

06 Jul 2022 Diag: Don Baldridge



We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

13 Dec 2021 Diag: Angela Borella

We recommend you service the filters on this component. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.








OIL ANALYSIS REPORT

North Plant-Crystallization PU-2512J Component

Hydraulic System

HIGH PERFORMANCE LUBRICANTS HYDRAULIC LIFE 46 (20 GAL)



DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


					1110070000 :	11/00000000
Sample Number		Client Info		WC0786776	WC0723604	WC0686369
Sample Date		Client Info		10 Aug 2023	23 Jan 2023	06 Jul 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	ATTENTION	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1	<1	<1
Chromium	ppm	ASTM D5185m	>10	1	0	0
Nickel	ppm	ASTM D5185m	>10	<1	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>10	0	0	0
Lead	ppm	ASTM D5185m	>10	<1	<1	<1
Copper	ppm	ASTM D5185m	>75	2	<1	<1
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		1	<1	0
Calcium	ppm	ASTM D5185m		63	67	68
Phosphorus	ppm	ASTM D5185m		396	397	388
Zinc	ppm	ASTM D5185m		417	427	414
Sulfur	ppm	ASTM D5185m		19369	19641	21278
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	<1	<1	<1
Sodium	ppm	ASTM D5185m		0	0	1
Potassium	ppm	ASTM D5185m	>20	1	<1	0
Water	%	ASTM D6304		0.006	0.003	0.012
ppm Water	ppm	ASTM D6304	>1000	67.5	29.1	123.6
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>640	A 2368	A 861	1263
Particles >6µm		ASTM D7647	>160	<u> </u>	<u> </u>	A 371
Particles >14µm		ASTM D7647	>40	<u> </u>	24	4 4
Particles >21µm		ASTM D7647	>10	<u> </u>	7	1 1
Particles >38µm		ASTM D7647	>3	0	0	0
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>16/14/12	A 18/16/13	▲ 17/15/12	▲ 17/16/13
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.56	0.54	0.52
14:04:26) Rev: 1 Submitted By: Alan I						



OIL ANALYSIS REPORT








MOLIAI			11 11 11			
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	50.8	48.8	48.2
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					THE REAL PROPERTY OF	



Bottom



Submitted By: Alan Brittain