

## **OIL ANALYSIS REPORT**

### North Plant-Purification **AG-32516** Component

**Gear Reducer ROYAL PURPLE SYNFILM GT 320 (30 GAL)** 

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

#### Fluid Condition

Viscosity of sample indicates oil is within ISO 220 range, advise investigate. Confirm oil type. The AN level is acceptable for this fluid.





NORMAL

SAMPLE INFORMATION method WC0804712 WC0765962 Client Info WC0527594 Sample Number 10 Aug 2023 20 Jan 2023 06 Jul 2022 Sample Date Client Info 0 0 0 Machine Age hrs **Client Info** Oil Age hrs Client Info 0 0 0 Oil Changed **Client Info** N/A N/A N/A NORMAL NORMAL Sample Status NORMAL WEAR METALS 5 ASTM D5185m >250 4 4 Iron ppm 0 0 Chromium ppm ASTM D5185m >5 0 0 0 Nickel ppm ASTM D5185m >5 0 Titanium ASTM D5185m 0 0 0 ppm 0 0 Silver ppm ASTM D5185m 0 Aluminum ASTM D5185m >20 0 0 <1 ppm Lead ASTM D5185m >50 0 0 <1 ppm Copper ASTM D5185m >50 <1 <1 ppm <1 0 Tin ppm ASTM D5185m >5 0 0 Antimony ASTM D5185m >5 ppm ---Vanadium ppm ASTM D5185m 0 0 0 Cadmium ASTM D5185m 0 0 0 ppm Boron ppm ASTM D5185m 0 0 0 0 Barium ASTM D5185m 1 1 ppm Molvbdenum ASTM D5185m n 0 0 nnm

Morybuenum	ppin	AGTIVI DJ TOJITI		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	90	73	82	74
Calcium	ppm	ASTM D5185m		<1	<1	0
Phosphorus	ppm	ASTM D5185m		5	7	5
Zinc	ppm	ASTM D5185m		5	5	2
Sulfur	ppm	ASTM D5185m		20907	17998	19492
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>60	<1	<1	0
Sodium	ppm	ASTM D5185m		0	0	0

Potassium	ppm	ASTM D5185m	>20	1	<1	<1
Water	%	ASTM D6304	>0.2	0.042	0.012	0.029
ppm Water	ppm	ASTM D6304	>2000	429.9	126.8	293.9
FLUID CLEANLIN	IECO	method	limit/base			history?
I LOID GLEANLIN	NESS	method	iiiiii/base	current	history1	history2
Particles >4µm	NESS	ASTM D7647	>20000	10840	3425	1363
	NESS				,	

Particles >6µm	ASTM D7647	>5000	3284	554	193
Particles >14µm	ASTM D7647	>640	284	46	28
Particles >21µm	ASTM D7647	>160	60	11	7
Particles >38µm	ASTM D7647	>40	2	0	0
Particles >71µm	ASTM D7647	>10	1	0	0
Oil Cleanliness	ISO 4406 (c)	>21/19/16	21/19/15	19/16/13	18/15/12

FLUID DEGRADATION Acid Number (AN)

mg KOH/g ASTM D8045 0.25

0.42

0.46


Report Id: AJIEDD [WUSCAR] 05926122 (Generated: 08/17/2023 14:06:02) Rev: 1


Submitted By: Alan Brittain


0.46



# **OIL ANALYSIS REPORT**







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	222	221	221
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color						
Bottom					$\bigcirc$	

