


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



AIR BLOWER 3

Component

Blower

HDZ-46 (60 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


2009 Jan2010 Aug2011 Sap2013 Aug2015 Aug2017 Aug2019 Sap2021									
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		WC0822377	WC0755604	WC0700512			
Sample Date		Client Info		11 Aug 2023	20 Nov 2022	06 Aug 2022			
Machine Age	hrs	Client Info		51518	49422	48967			
Oil Age	hrs	Client Info		0	0	0			
Oil Changed		Client Info		N/A	N/A	N/A			
Sample Status				NORMAL	NORMAL	NORMAL			
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>20	0	0	0			
Chromium	ppm	ASTM D5185m	>20	0	0	0			
Nickel	ppm	ASTM D5185m	>20	0	0	0			
Titanium	ppm	ASTM D5185m		<1	0	0			
Silver	ppm	ASTM D5185m		0	0	1			
Aluminum	ppm	ASTM D5185m	>20	0	<1	0			
Lead	ppm	ASTM D5185m	>20	<1	2	1			
Copper	ppm	ASTM D5185m	>20	15	15	19			
Tin	ppm	ASTM D5185m	>20	0	0	0			
Vanadium	ppm	ASTM D5185m		<1	0	0			
Cadmium	ppm	ASTM D5185m		<1	0	<1			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		0	0	0			
Barium	ppm	ASTM D5185m		0	0	2			
Molybdenum	ppm	ASTM D5185m		0	0	0			
Manganese	ppm	ASTM D5185m		<1	0	0			
Magnesium	ppm	ASTM D5185m		2	<1	0			
Calcium	ppm	ASTM D5185m		21	15	16			
Phosphorus	ppm	ASTM D5185m		306	305	278			
Zinc	ppm	ASTM D5185m		400	356	341			
Sulfur	ppm	ASTM D5185m		4245	4483	3719			
CONTAMINANTS		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>15	<1	<1	<1			
Sodium	ppm	ASTM D5185m		2	1	2			
Potassium	ppm	ASTM D5185m	>20	2	0	0			
FLUID DEGRADA	TION	method	limit/base	current	history1	history2			
Acid Number (AN)	mg KOH/g	ASTM D8045		0.40	0.41	0.41			
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE	VLITE	NONE			
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE	NONE	NONE			
Debris	scalar	*Visual	NONE	LIGHT	VLITE	LIGHT			
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML	NORML	NORML			
Emulsified Water	scalar	*Visual		NEG	NEG	NEG			
Free Water	scalar	*Visual		NEG	NEG	NEG			
1:00:20) Rov: 1				Contact/Locatio	n MICHAEL GE	DING LAMBAR			





OIL ANALYSIS REPORT





FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		43.8	41.6	41.9
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
Bottom						















Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 05926774

: WC0822377 : 10606721

Received Diagnosed

: 16 Aug 2023 : 18 Aug 2023 Diagnostician : Don Baldridge

Test Package : IND 2 (Additional Tests: KF)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) LAMB WESTON/RDO

PO BOX 552 PARK RAPIDS, MN US 56470

Contact: MICHAEL GRUIS michael.gruis@lambweston.com

T: (218)732-2188

F: (218)732-2175